



3202 34th Street, Valley, AL 36854

Telephone: 334-768-1262 or 1-800-554-7424 FAX: 334-768-1255

Textest Report: 1206631A
Date: 10/15/08
Page: 1 of 1

CLIENT: GLOBAL PLASTIC SHEETING
1331 Specialty Drive
Vista, CA 92081

ATTN: Kenneth Aguilar/Lee Hinsley

SAMPLE IDENTIFICATION: 8 MIL BLACK FR POLYETHYLENE

NFPA 701 (2004) TEST 1 FLAMMABILITY		Mass Before Test (grams)	Mass After Test (grams)	Mass Loss %	Drip Burn (Seconds)	After Flame (Seconds)
SPECIMEN *	#1	12.43	10.13	18.50	0.0	0.0
	#2	12.30	9.04	26.50	0.0	0.0
	#3	12.16	9.21	24.26	0.0	0.0
	#4	12.24	8.91	27.21	0.0	0.0
	#5	12.26	9.05	26.18	0.0	0.0
	#6	12.56	8.95	28.74	0.0	0.0
	#7	12.28	9.84	19.87	0.0	0.0
	#8	12.32	9.02	26.79	0.0	0.0
	#9	12.26	9.08	25.94	0.0	0.0
	#10	12.42	8.96	27.86	0.0	0.0
Average				25.18	0.0	
Avg. + 3 Std. Dev.				35.36		

* Specimens were conditioned at least 24 hours at 20±5°C before testing.

CRITERIA: PASS/FAIL

MASS LOSS: 40% Max. Avg. or
Avg. + 3 Standard Deviations Max. Ind.

DRIP BURN: 2 Seconds Max. Avg.

COMMENTS: The submitted sample passes the requirements of NFPA 701 (2004)
Test 1 Flammability.

TEXTTEST

Signed by