

# Generic Paint Specification 3029 for Colorbond Cladding

**Description:** - This specification outlines the use of Enviroflon 8480 for application to Colorbond. Enviroflon 8480 is a water borne two pack fluoropolymer coating featuring excellent long term UV stability and colour retention. Enviroflon 8480 also provides a hard wearing surface, an excellent appearance and excellent graffiti resistance. Enviroflon 8480 is available in any colour, and a gloss or satin finish.

**Application:** - Colorbond Cladding

**Product:**

1. Envirothane 8480 Water Borne Two Pack Fluoropolymer

**Process:**

Details	Theoretical Coverage
1. Clean in accordance with AS1627.1 to remove all degreasing products, grease, dirt, salts and other contaminants and lightly abrade.	
2. Apply in two coats wet-on-wet Enviroflon 8480 Topcoat to a minimum dry film thickness of 50 microns.	8m <sup>2</sup> /L

**Notes:**

1. Coverage rates depend to a large extent on the method of application and also the continuity of surface being coated.
2. Specification is subject to Architectural & Industrial Coatings doing an adhesion test on the exact Colorbond substrate to be coated.

---

**This Generic Paint Specification must be read having regard to the Notes below.**

Notes:

This specification is a generic specification. This specification must be read in conjunction with all relevant Product Data Sheets and Safety Data Sheets. This specification is offered free of charge and as a guide only. To the extent permitted by law, A&I Coatings liability with respect to the Products is limited to supply of replacement materials and no further liability for failure of the Product or associated costs will be borne by A&I Coatings. Being a generic specification, there may be situations or conditions not considered that could influence the performance or appearance of the finished product. You must ensure this specification is suitable for your project by contacting your A&I Coatings representative prior to purchasing the Product. Product usage rates given in this specification are an indication only and do not allow for any wastage or variation due to factors beyond the control of A&I Coatings.

A&I Coatings Pty Ltd t/as A&I Coatings (ABN 55 161 784 185)

Address: 7 Lackey Road (PO BOX 820) Moss Vale NSW 2577 Australia

Phone: 61 2 4869 1441 / Fax: 61 2 4869 3031 / Email: helpdesk@aicoatings.com / Web: www.aicoatings.com

This specification prepared By: Peter Gillies / Approved By: Frank Jiang / QAF037 Version Number: 01 / Issue Date: 30/03/10