ASAGLEAN PX2 GRADE

Purging Compound for thermoplastic injection molding and extrusion applications

- High Temperature
 Glass-Filled
- Superior Cleaning Power* (Compared to PX Grade)
- Low Processing Smoke and Odor
- Excellent Thermal Stability at High Processing Temperatures

Resins Purged:

Exclusively used for purging super-engineering resins such as PPS, PEEK, LCP, PEI.

Processing
Temperature:
280°C to 420°C
(535°F to 790°F)

S	Color Changes	~
2 0	Material Changes	V
	Hot Runner Cleaning	
A	Shutdown / Sealing	
Ö	Clear / Low Residue Applications	
_	Low Temperature Resins	
<u>م</u>	High Temperature Resins	V
<u>а</u>	Carbon / Color Contamination	V

PX2

Tips when using ASACLEAN:

- ASACLEAN does not work by chemical reaction.
- No soak time or hold-up time is required for an effective purge.
- For maximum performance, ASACLEAN should not be diluted with other materials.
- ASACLEAN works best with maximum agitation. Use the maximum safe screw speed.
- For injection molding, also use maximum safe back pressure with the screw in the most forward position.

Purging Compound for thermoplastic injection molding and extrusion applications

ASACLEAN PX2 Grade excels in purging super-engineering resins at processing temperatures of up to 420°C (790°F). PX2 Grade is the most powerful high temperature grade for cleaning hard-to-clean resins. PX2 Grade generates low levels of smoke and odor across the entire operating temperature range of 280°C-420°C (535°F-790°F).

The photos illustrate the different amounts of purge required when using PX versus PX2. Testing was performed using PEI (Black) at 380°C (720°F) on a 50-ton injection molding machine. Note that PX2 (right) required far less material than PX (left).

* The above values are obtained from our laboratory tests and should be used as reference only.



Purged with PX Grade - Used 450g (16 oz.)



Purged with PX2 Grade - Used 350g (12 oz.)

Tips for purging with ASACLEAN PX2 Grade:

- ASACLEAN PX2 Grade should not be left idle in the machine at any temperature for any period of time.
- For nozzle hang-up or check ring cleaning (carbon and/or color deposits), use short, high-velocity shots.
- Do NOT use for hot runner cleaning and sealing due to its glass content.



Call Us For a FREE Sample at (800) 787-4348 or Outside USA / Canada (973) 257-1999

Sun Plastech Incorporated 1055 Parsippany Blvd., Parsippany, NJ 07054
Tel: (800) 787-4348 • Fax: (973) 257-1011 • Email: sales@asaclean.com • Website: www.asaclean.com