

ASACLEAN™ U GRADE

Purging Compound for thermoplastic injection molding and extrusion applications

- High Performance General Purpose
- Styrenic-Based

U Grade's cleaning power approaches that of our strongest scrubber, EX Grade, but without the glass filler. It is ideal for applications that require higher detergency while maintaining lower residue.

RESINS PURGED:

Most commodity and engineering resins within the processing temperature range.

Processing Temperature:
180°C to 360°C
(350°F to 680°F)

U Grade requires 0.020" (0.5 mm) clearance for hot runner gates and extrusion dies; 100-mesh is required for extrusion screen packs.

Tips when using ASACLEAN:

A P P L I C A T I O N S	Color Changes	✓
	Material Changes	✓
	Hot Runner Cleaning	✓
	Shutdown / Sealing	✓
	Clear / Low Residue Applications	
	High Temperature Resins	
	Low Temperature Resins	
	Carbon / Color Contamination	✓

- ASACLEAN does not work by chemical reaction.
- No soak time or hold-up time is required for an effective purge.
- For maximum performance, ASACLEAN should not be diluted with other materials.
- ASACLEAN works best with maximum agitation. Use the maximum safe screw speed and for injection molding also use maximum safe back pressure with the screw in the most forward position.

Purging Compound for thermoplastic injection molding and extrusion applications

▶ Usage Example: Nylon color change

The photo series below shows purge piles from black to natural Nylon color changes with and without the use of **ASACLEAN U Grade**.

WITHOUT ASACLEAN

[Machine: 200-ton injection molding machine at 530°F - Total purge time: 30 minutes]
Purge piles shown are in 5-minute intervals.



WITH ASACLEAN

[Machine: 200-ton injection molding machine at 530°F - Total purge time: 10 minutes]



ASACLEAN™

AsahiKASEI

Call Us For a **FREE** Sample at (800) 787-4348 or Outside USA / Canada (973) 257-1999

Sun Plastech Incorporated 1055 Parsippany Blvd., Parsippany, NJ 07054

Tel: (800) 787-4348 • Fax: (973) 257-1011 • Email: sales@asaclean.com • Website: www.asaclean.com

Sun Plastech Inc. manufactures and distributes ASACLEAN™ Purging Compound, a respected name in over 70 countries around the world. Established in 1996, the company serves thermoplastic injection molders and extruders across North and South America. Sun Plastech is backed by the technology and resources of its parent company, one of the world's leading chemical companies, Asahi Kasei Corp. Asahi Kasei is an ISO9001 and ISO14001 certified company.