

**TRELLEBORG COATED SYSTEMS US, INC.****07050**

EXCELLENCE THROUGH INNOVATION

**.030" Black Nitrile/Antiwickling Nylon**

<b>COATED FABRIC PROPERTIES</b>	<b>Test Method</b>	<b>REQUIREMENTS</b>
Adhesion	ASTM D 751-89, sec. 43.1.2	Minimum of 10.00 lbs/inch
Color	Visual	Black
Curl test	Trelleborg Test Method	Maximum of 0.25 inches
Gauge	ASTM D 751-89, sec. 9	Range of 0.028 to 0.032 inches
Antiwickling	Trelleborg Test Method	Minimum of 100.00 psi
Mullen Burst	ASTM D 751-89, sec. 18.3	Minimum of 700.00 psi
Strip Tensile - Fill	ASTM D 751-89, sec. 16	Minimum of 225.00 lbs
Strip Tensile - Warp	ASTM D 751-89, sec. 16	Minimum of 250.00 lbs
Durometer - Shore A (Cmpd Only)	ASTM D 2240	50-60

**Product complies with with ASTM D2000 2CH615E3SZ smooth finish**

Original Date: 11/30/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.  
 715 Railroad Avenue  
 Rutherfordton, NC 28139  
 1-800-635-9350 - fax (828) 394-5005



Original Date: 11/30/2015

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Trelleborg Coated Systems US, Inc., makes no guarantee of results and assum