

bpi brentwood plastics, inc.

8734 SUBURBAN TRACKS • ST. LOUIS • MISSOURI • 63144

Phone 314) 968-1135 • www.brentwoodplastics.com • Fax 314) 968-4276

SHRINK

SHRINK is an industrial shrink bundling film made for packaging bottles, canned goods, bagged pet food and corrugated boxes. Unless otherwise specified, targeted MD shrink is 68% and TD is 3% to ensure a tight "bull's eye" closure on the package side. Low slip means cases can be stacked without sliding.

<u>Properties</u>	<u>test method</u>	<u>typical value*</u>	<u>unit</u>
Haze	ASTM D 1003	19	%
Gloss 45 °	ASTM D 2457	46	-
1% secant modulus	MD TD	27,200 32,300	psi
Dart Impact F50	ASTM D1709A	260	gm.
Elmendorf tear	MD TD	450 610	gm.
Tensile Break Strength	MD TD	4,100 3,950	psi
Tensile Elongation @ break	MD TD	520 630	% %
Tensile Yield	MD TD	1,580 1,470	psi psi
Elongation @ yield	MD TD	19.6 13.1	% %

* data obtained on 2.0 mil film is typical and not to be construed as specification limits. Establishing suitability for any end use is the end user's responsibility. No warranties are expressed or implied.