

Pelseal Technologies' state-of-the-art fluid coatings, caulks, adhesives and sealants are manufactured from fluoroelastomer rubber. Our products resist attack, to varying degrees, by a broad spectrum of industrial chemicals, fuels, oils, and other substances.

We have researched the effect of the listed chemicals on fluoroelastomers at various temperatures, concentrations, and exposure times. Our information is based on extensive laboratory tests and experiments that have been performed on fluoroelastomers themselves by a number of outside organizations, including manufacturers, end users, suppliers, and trade associations.

The information is believed to be reliable. However, the degree of fluid resistance of an elastomer to deterioration by a specific substance is dependent on many variables, including the concentration and temperature of the material; the frequency and duration of exposure; the velocity of flow and aeration; mechanical action; and the ratio of contact

surface area to volume. Therefore, the ratings in the accompanying listing should be used only as a general guide, not as specific recommendations.

While the information is presented by us in good faith, no guarantee, expressed or implied, can be given regarding the accuracy of these ratings.

In those cases where no data are available, the rating shown is the considered, conditional opinion of experienced rubber chemists and compounders.

We strongly urge you to test our products under actual or simulated service conditions, before you purchase them, rather than assume that they will perform satisfactorily in your specific application. In order to assist you in learning more about the chemical resistance of Pelseal's products to the substance shown, the following rating code has been used:

CODE

E	Excellent Resistance - little or minor attack by the material on fluoroelastomers; 0-5% volume swell where applicable.
G	Good Resistance - minor to moderate attack by the material on fluoroelastomers; 5-10% volume swell where applicable.
F	Fair Resistance - moderate to severe attack by the material on fluoroelastomers; 10-20% volume swell where applicable.
NR	Not Recommended.
COK	No Data Available - our conditional opinion is that fair to excellent resistance by fluoroelastomers is likely to occur.
CNR	No Data Available - our conditional opinion is that severe attack by the material on fluoroelastomers is likely to occur.

Chemical	Rating	Chemical	Rating	Chemical	Rating
Acetaldehyde	NR	Air	E	Aluminum Sodium Chloride	E
Acetamide (<120°F)	G	Alkazene (Dibromoethylbenzene)	G	Aluminum Sulfate	E
Acetic Acid (0-15%)	G	Allyl Alcohol	G	Ammonia, Anhydrous	NR
Acetic Acid, 30%	F	Allylamine (0-50%)	NR	Ammonia, Wet	NR
Acetic Acid, 50%	F	Allyl Bromide	E	Ammonium Acetate	NR
Acetic Acid, Glacial	NR	Allyl Chloride	E	Ammonium Benzoate	COK
Acetic Anhydride	NR	Aluminum Acetate	COK	Ammonium Bicarbonate	E
Acetone	NR	Aluminum Bromate	COK	Ammonium Carbonate	E
Acetonitrile	NR	Aluminum Bromide	E	Ammonium Chloride	E
Acetophenone	NR	Aluminum Chloride	E	Ammonium Chlorostanate	COK
Acetyl Chloride	E	Aluminum Fluoride (25%)	E	Ammonium Dichromate	COK
Acetylene	E	Aluminum Hydroxide	G	Ammonium Fluoride (25%)	COK
Acrylamide (0-5%)	CNR	Aluminum Iodide	E	Ammonium Hydroxide (0-30%)	G
Acrylonitrile	NR	Aluminum Nitrate	E	Ammonium Iodate	COK
Adipic Acid Solution	COK	Aluminum Phosphate	E	Ammonium Iodide	COK

Chemical	Rating	Chemical	Rating	Chemical	Rating
Ammonium Nitrate	E	Barium Nitrite	COK	Butyl Stearate	E
Ammonium Nitrite	COK	Barium Oxalate	COK	Butylene	E
Ammonium Oxalate	COK	Barium Sulfate	E	Butyraldehyde	NR
Ammonium Persulfate	E	Barium Sulfide	E	Butyric Acid	G
Ammonium Phosphate	G	Barium Sulfite	COK	Butyronitrile	CNR
Ammonium Silicate	COK	Beer	E	Cadmium Bromate	COK
Ammonium Sulfate	G	Benzaldehyde	NR	Cadmium Bromide	COK
Ammonium Sulfide	G	Benzene	E	Calcium Acetate	NR
Ammonium Thiosulfate	G	Benzene (5% in Kerosene)	E	Calcium Bisulfate	E
Ammonium Trichloride	COK	Benzene Sulfonic Acid	E	Calcium Bisulfite	E
Amyl Acetate (Banana Oil)	NR	Benzoic Acid	E	Calcium Bromate	COK
Amyl Acid Phosphate	COK	Benzoyl Chloride	E	Calcium Bromide	COK
Amyl Alcohol	G	Benzyl Alcohol	E	Calcium Carbonate	E
Amyl Amine	NR	Benzyl Benzoate	E	Calcium Chlorate	E
Amyl Borate	E	Benzyl Chloride	E	Calcium Chloride	E
Amyl Bromide	G	Beverages, Carbonated	E	Calcium Citrate	COK
Amyl Chloride	E	Biphenyl	E	Calcium Hydroxide (0-50%)	E
Amyl Chloronaphthalene	E	Bismuth Oxychloride	COK	Calcium Hypochlorite (0-20%)	E
Amyl Ether	CNR	Black Liquor	E	Calcium Iodide	COK
Amyl Iodide	COK	Bleach (0-6%)	E	Calcium Nitrate	E
Amyl Naphthalene	E	Bleach Liquor	E	Calcium Nitrite	COK
Amylene	G	Blood	E	Calcium Oxychloride	COK
Aniline	F	Borax	E	Calcium Phosphate	E
Aniline Hydrochloride	G	Boric Acid	E	Calcium Sulfate	G
Animal Fats	E	Brine (salt water)	E	Calcium Sulfide	E
Ansul Ether	NR	Bromic Acid	COK	Calcium Sulfite	E
Antifreeze (Glycol Base)	G	Bromine	E	Calcium Thiosulfate	E
Antimony Trichloride	G	Bromine, Anhydrous	E	Carbamate	E
Arsenic Acid (0-75%)	E	Bromine Trifluoride	NR	Carbitol	G
Arsenic Trichloride	NR	Bromine Water	E	Carbon Dioxide	G
Askarel	E	Bromobenzene	E	Carbon Disulfide	E
Asphalt	E	Bromochloromethane	F	Carbon Monoxide	E
ASTM Fuel A	E	Bunker Oil	E	Carbon Tetrachloride	E
ASTM Fuel B	E	Butadiene	E	Carbon Tetrafluoride	E
ASTM Fuel C	E	Butane	E	Carbonic Acid	E
ASTM No. 1 Oil	E	Butter	E	Castor Oil	E
ASTM No. 2 Oil	E	Butyl Acetate	NR	Cellosolve	NR
ASTM No. 3 Oil	E	Butyl Acetyl Ricinoleate	E	Cellosolve Acetate	NR
Banana Oil (Amyl Acetate)	NR	Butyl Acrylate	NR	China Wood Oil (Tung Oil)	E
Bardol B	G	Butyl Alcohol	E	Chlorine Dioxide	E
Barium Bromide	COK	Butyl Aldehyde	NR	Chlorine, Dry Gas	E
Barium Carbonate	E	Butyl Amine	NR	Chlorine, Trifluoride	NR
Barium Chlorate	COK	Butyl Benzoate	E	Chlorine Water	E
Barium Chloride	E	Butyl Carbitol	E	Chlorine, Wet Gas	E
Barium Citrate	COK	Butyl Cellosolve	NR	Chloroacetic Acid	NR
Barium Dichromate	COK	Butyl Ether	NR	Chloroacetone	NR
Barium Hydroxide (0-10%)	E	Butyl Iodide	COK	Chloroacetonitrile	CNR
Barium Iodate	COK	Butyl Mercaptan	E	Chlorobenzene	E
Barium Iodide	COK	Butyl Oleate	E	Chlorobromomethane	E
Barium Nitrate	E	Butyl Phthalate	F	Chlorobutadiene	E

Chemical	Rating	Chemical	Rating	Chemical	Rating
Chlorododecane	E	Detergents, All	E	Dioxolane	NR
Chloroethyl Benzene	E	Diacetone Alcohol	NR	Dipentene	E
Chloroform	E	Diallylamine	CNR	Diphenyl	E
Chloronaphthalene	E	Dibenzyl Ether	NR	Diphenyl Oxides	E
1-Chloro-1-Nitroethane	NR	Dibenzyl Sebacate	F	Disodium Phosphate	COK
Chlorostannic Acid	COK	Dibromoethylbenzene (Alkazene)	G	Di-Tert-Butyl Peroxide	CNR
Chlorosulfonic Acid	NR	Dibutyl Acetate	CNR	Divinyl Benzene	E
Chlorotoluene	E	Dibutyl Amine	NR	Epichlorohydrin	NR
Chrome Plating Solution	E	Dibutyl Ether	F	Epsom Salt	G
Chromic Acid (0-66%)	E	Dibutyl Phthalate	F	Ethane	E
Chromic Sulfate	COK	Dibutyl Sebacate	F	Ethanolamine	NR
Chromium Potassium Sulfate	E	Dichloroacetic Acid	NR	Ether	F
Chromous Chloride	COK	1,4-Dichloro-2-butene	COK	Ethyl Acetate	NR
Chromous Iodide	COK	3,4-Dichloro-1-butene	COK	Ethyl Acrylate (100%)	NR
Citric Acid	E	Dichloro-Difluoro Methane	F	Ethyl Alcohol	G
Coal Tar (Creosote)	E	Dichloroethane	E	Ethyl Benzene	E
Cobalt Chloride	E	Dichloro-Fluoro Methane	NR	Ethyl Benzoate	E
Coconut Oils	E	Dichloro-Isopropyl Ether	F	Ethyl Bromide	G
Cod Liver Oil	E	Dichloromethane	F	Ethyl Butyrate	F
Coke Oven Gas	E	Dicyclohexylamine	NR	Ethyl Caprylate	COK
Copper Acetate	NR	Dicyclopentadiene	COK	Ethyl Cellosolve	NR
Copper Chloride	E	Diesel Fuel	E	Ethyl Cellulose	NR
Copper Cyanide	E	Diethanolamine	NR	Ethyl Chloride	E
Copper Fluoride	COK	Diethylamine	NR	Ethyl Chlorocarbonate	E
Copper Nitrate	COK	Diethyl Benzene	E	Ethyl Chloroformate	G
Copper Sulfate	E	Diethyl Carbonate	G	Ethyl Ether	NR
Corn Oil	E	Diethyl Ether	NR	Ethyl Formate	E
Cottonseed Oil	E	Diethyl Ketone	NR	Ethyl Hexanoate	COK
Creosote (Coal Tar)	E	Diethyl Phthalate	F	Ethyl Hexanol	E
Cresol	E	Diethyl Sebacate	COK	Ethyl Iodide	E
Cresylic Acid	E	Diethyl Sulfate	NR	Ethyl Isobutyl Ether	CNR
Crude Oil, Sour	E	Diethylene Glycol	E	Ethyl Isobutyrate	COK
Crude Oil, Sweet	E	Diisobutylene	E	Ethyl Mercaptan	F
Cumene	E	Diisopropyl Benzene	E	Ethylmorpholine	COK
Cupric Bromate	COK	Diisopropyl Ether	CNR	Ethyl Oxalate	G
Cupric Bromide	COK	Diisopropyl Ketone	NR	Ethyl Pentachloro-Benzene	E
Cupric Chloride	E	Diisopropylidene		Ethyl Propionate	COK
Cupric Hydroxide	F	Acetone (Phorone)	NR	Ethyl Propyl Ether	CNR
Cupric Sulfate	E	Dimethylamine	CNR	Ethyl Silicate	E
Cuprous Sulfite	COK	Dimethyl Aniline (Xylidene)	NR	Ethylene	E
Cuprous Thiocyanate	COK	Dimethylcyclohexylamine	CNR	Ethylene Chloride	G
Cyclohexane	E	Dimethyl Ether	E	Ethylene Chlorohydrin	E
Cyclohexanol	E	Dimethyl Formamide	NR	Ethylenediamine	NR
Cyclohexanone	NR	Dimethyl Phthalate	G	Ethylene Dibromide	G
Cyclopentane	COK	Dimethyl Sulfate	NR	Ethylene Dichloride	E
Cymene, Para	E	Dinitrobenzene	E	Ethylene Glycol	E
Decahydronaphthalene	E	Dinitrotoluene	NR	Ethylene Oxide	NR
Decane	E	Diethyl Adipate	F	Ethylene Trichloride	E
Deionized Water	E	Diethyl Phthalate	G	Fatty Acids	E
Denatured Alcohol	G	Diethyl Sebacate	E	Ferric Bromide	E
		Dioxane	NR		

Chemical	Rating	Chemical	Rating	Chemical	Rating
Ferric Chloride	E	Hydrogen Bromide	E	Magnesium Chloride	E
Ferric Formate	COK	Hydrogen Gas	E	Magnesium Hydroxide	E
Ferric Nitrate	E	Hydrogen Peroxide (0-35%)	E	Magnesium Nitrate	E
Ferric Oxalate	COK	Hydrogen Sulfide, Aqueous	NR	Magnesium Perchlorate	COK
Ferric Sulfate	E	Hydroquinone	F	Magnesium Sulfate	E
Ferric Sulfide	COK	Hypochlorous Acid (0-10%)	E	Magnesium Thiosulfate	COK
Ferric Thiocyanate	COK	Iodine	G	Maleic Acid (100%)	E
Ferrous Chloride	E	Iodine Pentafluoride	NR	Maleic Anhydride	NR
Ferrous Chloroplatinate	COK	Iodoform	COK	Malic Acid	E
Ferrous Ferricyanide	COK	Isoamyl Acetate	NR	Malonyl Nitrile	CNR
Ferrous Fluoride	COK	Isoamyl Alcohol	G	Manganese Chloride	G
Ferrous Formate	COK	Isobutyl Acetate	NR	Manganese Iodide	COK
Ferrous Iodide	COK	Isobutyl Alcohol	E	Manganese Lactate	COK
Ferrous Perchlorate	COK	Isododecane	G	Manganese Sulfate	E
Ferrous Potassium Oxalate	COK	Isooctane	E	Mercuric Cyanide	COK
Ferrous Sulfate	E	Isopentane	G	Mercurous Nitrate	COK
Ferrous Thiocyanate	COK	Isophorone	NR	Mercury	E
Ferrous Thiosulfate	COK	Isopropyl Acetate	NR	Mercury Chloride	E
Fish Oil	E	Isopropyl Alcohol	E	Mesityl Oxide	NR
Fluoboric Acid (0-50%)	G	Isopropyl Benzene	E	Methane	E
Fluorine	G	Isopropyl Biphenyl	COK	Methyl Acetate	NR
Fluorobenzene	E	Isopropyl Chloride	E	Methylacrylate	NR
Fluosilicic Acid (0-32%)	E	Isopropyl Ether	NR	Methylacrylic Acid	G
Formaldehyde (0-40%)	F	Jet Fuel JP-3	E	Methyl Alcohol	G
Formamide	NR	Jet Fuel JP-4	E	Methyl Amine	CNR
Formic Acid	F	Jet Fuel JP-5	E	Methylamyl Acetate	NR
Fuel Oil	E	Kerosene	E	Methylamyl Alcohol	COK
Fumaric Acid (0-55%)	E	Lactic Acid (0-88%)	E	Methyl Aniline	CNR
Furfural	NR	Lactol	E	Methyl Bromide	E
Furfuran	CNR	Lard	E	Methyl Butyrate	CNR
Gallic Acid	E	Lauric Acid	COK	Methyl Cellosolve	NR
Gasoline Refined, All	E	Lavender Oil	E	Methyl Chloride	G
Gelatin	E	Lead Acetate	NR	Methyl Cyclopentane	E
Glucose	E	Lead Chloride	E	Methyl Ether	F
Glycerine	E	Lead Fluoborate (0-48%)	COK	Methyl Ethyl Ketone	NR
Glyoxal	CNR	Lead Nitrate	E	Methyl Formate	NR
Grease, Silicone	COK	Lead Persulfate	COK	Methyl Iodide	COK
Heptanal	NR	Lead Sulfamate	E	Methyl Isobutyl Carbinol	COK
Heptane	E	Lead Sulfate	E	Methyl Isobutyl Ketone	NR
Hexaldehyde, Normal	NR	Levulinic Acid (25%)	CNR	Methyl Methacrylate	NR
Hexane	E	Ligroin (Petroleum Ether)	E	Methyl Oleate	F
Hexene	E	Linoleic Acid	G	Methyl Salicylate	COK
Hexyl Alcohol	E	Linseed Oil	E	Methylene Chloride	F
Hydraulic Fluid	E	Liquified Petroleum Gas (LPG)	E	Milk	E
Hydrazine, 35% Catalyzed	NR	Lithium Acetate	NR	Mineral Oils	E
Hydrobromic Acid (0-50%)	E	Lithium Nitrate	COK	Mineral Spirits	E
Hydrochloric Acid (0-37%)	E	Lithium Sulfide	COK	Molasses	E
Hydrocyanic Acid	E	Magnesium Acetate	NR	Molybdenum Oxybromide	COK
Hydrofluoric Acid	E	Magnesium Bromide	COK	Molybdenum Oxychloride	COK
Hydrofluosilicic Acid	E	Magnesium Carbonate	E	Molybdenum Tetrabromide	COK

Chemical	Rating	Chemical	Rating	Chemical	Rating
Monobromobenzene	E	Petroleum Oils	G	Potassium Sulfate	E
Monochlorobenzene	E	Phenol	E	Potassium Sulfide	COK
Monoethanolamine	NR	Phenol Sulfonic Acid	E	Potassium Sulfite	E
Monomethyl Aniline	G	Phenylbenzene	E	Potassium Thiocarbonate	COK
Monomethylether	G	Phenyl Ethyl Ether	NR	Potassium Thiocyanate	COK
Monovinyl Acetylene	E	Phenylhydrazine	E	Propane Gas	E
Morpholine	COK	Phorone (Diisopropylidene Acetone)	NR	Propionic Acid	CNR
Naphtha	E	Phosphoric Acid (0-85%)	E	Propionitrile	NR
Naphthalene	E	Phosphorous Oxychloride	COK	Propyl Acetate	NR
Naphthalenic Acid	E	Phosphorous Trichloride	E	Propyl Acetone	NR
Naphthenic Acids	E	Pickling Acids, Sulfuric & Hydrochloric	E	Propyl Alcohol	E
Natural Gas	E	4-Picoline (0-50%)	CNR	Propyl Nitrate	NR
Neatsfoot Oil	E	Picric Acid	G	Propylene	E
Nickel Acetate	NR	Pinene	E	Propylene Dichloride	E
Nickel Bromide	COK	Pine Oil	E	Propylene Glycol	E
Nickel Chloride	E	Piperidine	NR	Propylene Oxide	NR
Nickel Formate	COK	Platinic Acid	COK	Pulp Mill Liquors	COK
Nickel Nitrate	COK	Platinum Chloride	COK	Pyridine	NR
Nickel Potassium Cyanide	COK	Platinum Sulfate	COK	Pyroligneous Acid	NR
Nickel Sulfate	E	Polyethylene Glycol	G	Pyrrole	NR
Nitric Acid	E	Polyvinyl Acetate	CNR	Rapeseed Oil	E
Nitrobenzene	G	Potassium Acetate	NR	Rhodium Chloride	COK
Nitroethane	NR	Potassium Aluminum Silicate	COK	Rhodium Sulfate	COK
Nitrogen Gas	E	Potassium Arsenate	COK	Rosin Oil	COK
Nitrogen Tetroxide	NR	Potassium Arsenite	COK	Salicylic Acid	E
Nitromethane	NR	Potassium Bicarbonate	E	Salt Water	E
Nitropropane	NR	Potassium Bisulfate	G	Selenic Acid	COK
Octachlorotoluene	E	Potassium Bisulfite	G	Silicate Esters	E
Octadecane	E	Potassium Borate	COK	Silicic Acid	E
Octane	E	Potassium Bromide	COK	Silicon Fluoride	COK
Octyl Alcohol	E	Potassium Carbonate	E	Silver Cyanide	COK
Oleic Acid	G	Potassium Chlorate	COK	Silver Nitrate	E
Oleyl Alcohol	COK	Potassium Chloride	E	Silver Perchlorate	COK
Olive Oil	E	Potassium Cyanate	COK	Silver Permanganate	COK
Orthodichlorobenzene	E	Potassium Cyanide	E	Silver Thiosulfate	COK
Oxalic Acid (12.5%)	E	Potassium Dichromate	E	Soap Solutions	E
Oxygen Gas - Cold	E	Potassium Fluoride	E	Sodium Acetate	NR
Ozone	E	Potassium Hydrosulfide	COK	Sodium Benzoate	COK
Palladium Chloride	COK	Potassium Hydroxide	F	Sodium Bicarbonate	E
Palmitic Acid	E	Potassium Hypochlorite	COK	Sodium Bisulfate	E
Paradichlorobenzene	G	Potassium Hypophosphite	COK	Sodium Bisulfite	E
Paraffin Wax	G	Potassium Iodide	COK	Sodium Borate	E
Paraldehyde	NR	Potassium Nitrate	E	Sodium Bromide	COK
Peanut Oil	E	Potassium Nitrite	COK	Sodium Carbonate	E
Pentachlorophenol	E	Potassium Permanganate	G	Sodium Chlorate (0-50%)	COK
Pentane	G	Potassium Phosphate, Hydrogen	COK	Sodium Chloride	E
2, 4-Pentanedione	CNR	Potassium Phosphate, Pyro	COK	Sodium Cyanide	E
Perchloric Acid	E	Potassium Phosphite	COK	Sodium Dichromate	E
Perchloroethylene	E	Potassium Silicate	COK	Sodium Ferrocyanide	COK
Petroleum Ether (Ligroin)	E			Sodium Fluoride	COK

Chemical	Rating	Chemical	Rating	Chemical	Rating
Sodium Hydroxide (0-50%)	G	Tertiary Butyl Alcohol	E	Turbine Oil	E
Sodium Hypochlorite (0-15%)	E	Tertiary Butyl Mercaptan	E	Turpentine	E
Sodium Metabisulfite (0-40%)	E	Tetrabromomethane	E	Undecyl Alcohol	G
Sodium Methoxide (30%)	COK	Tetrabutyl Titanate	E	Urea 50%	CNR
Sodium Nitrate	E	Tetrachloroethane	E	Urine	CNR
Sodium Nitrite	E	Tetrachloroethylene	E	Varnish	E
Sodium Perborate	E	Tetraethyl Lead	E	Vegetable Oils	E
Sodium Peroxide	E	Tetrahydrofuran (0-15%)	NR	Vinegar	E
Sodium Persulfate (55%)	COK	Tetrahydronaphthalene	G	Vinyl Acetate	NR
Sodium Phosphate	E	Thionyl Chloride	F	Vinyl Benzene	E
Sodium Silicate	E	Thiophene	F	Vinyl Chloride	E
Sodium Sulfate	E	Tin Fluoborate (0-48%)	COK	Vinyltrimethoxysilane	COK
Sodium Sulfide	E	Titanium Chloride	E	Water, Deionized	E
Sodium Sulfite (0-30%)	E	Titanium Fluoride	COK	Water, Distilled	E
Sodium Tetraborate	E	Titanium Nitrate	COK	Water, Salt	E
Sodium Thiosulfate	E	Titanium Tetrachloride	E	Whiskey	E
Soybean Oil	E	Toluene	E	White Oil	E
Stannic Chloride	E	Toluene Diisocyanate	NR	Wine	E
Stannous Chloride	E	Toluidine	E	Xylene	E
Steam	G	Triacetin	NR	Xylidene (Dimethyl Aniline)	NR
Stearic Acid	E	Triaryl Phosphate	E	Zeolites	E
Stoddard Solvent	E	Tributoxyethyl Phosphate	E	Zinc Acetate	NR
Styrene	G	Tributyl Mercaptan	E	Zinc Chloride	E
Sugar	E	Tributyl Phosphate	NR	Zinc Fluorosilicate	COK
Sulfamic Acid (0-25%)	E	Trichloroacetic Acid	F	Zinc Formate	COK
Sulfite Liquors	E	Trichloro Benzene	E	Zinc Permanganate	COK
Sulfur	E	1-1-1 Trichloroethane	E	Zinc Sulfate	E
Sulfur Chloride	E	Trichloroethylene	E		
Sulfur Dioxide, wet or dry	E	Trichlorotrifluoroethane	E		
Sulfur Hexafluoride	E	Tricresyl Phosphate	E		
Sulfur Trioxide	E	Triethanolamine	NR		
Sulfuric Acid (0-98%)	E	Triethyl Aluminum	G		
Sulfurous Acid	E	Triethyl Borane	E		
Tall Oil	E	Triethylene Glycol	G		
Tallow	E	Triethylenetetramine	NR		
Tannic Acid	E	Trinitrotoluene	G		
Tantalum Fluoride	COK	Trioctyl Phosphate	F		
Tar, Bituminous	E	Triphenyl Phosphate	F		
Tartaric Acid	E	Trisodium Phosphate	E		
Terpineol	E	Tung Oil (China Wood Oil)	E		

