

FACTORY-APPLIED COATING FOR METAL

PART 1 - GENERAL

1.1 SECTION INCLUDES

- A. This Section specifies factory-applied metal coatings including the following:
1. **Colorgalv® Marine Immersion** Hot-dip galvanizing with factory-applied high performance polyamide epoxy primer with high performance polyamide gloss epoxy coating system for iron and steel fabrications.

1.2 RELATED SECTIONS

- A. Examine Contract Documents for requirements that affect Work of this Section. Other Specification Sections that directly relate to Work of this Section include, but are not limited to:
1. Section 033000 - Cast-In-Place Concrete.
 2. Section 042000 - Unit Masonry.
 3. Section 051200 - Structural Steel Framing.
 4. Section 053000 - Metal Decking.
 5. Section 055000 - Metal Fabrications.
 6. Section 055100 - Metal Stairs.
 7. Section 055200 - Metal Railings.
 8. Section 057000 - Decorative Metal.
 9. Section 077100 - Roof Specialties.
 10. Section 107000 - Exterior Specialties.
 11. Section 107500 - Flagpoles.
 12. Section 129300 - Site Furnishings.
 13. Section 323000 - Site Improvements.
 14. Section 323100 - Fences and Gates.

1.3 SUBMITTALS

- A. Product Literature for Factory-Applied Metal Coatings: Submit galvanizer's product literature for coatings specified in this Section including test data.
- B. Verification Samples for Factory-Applied Metal Coatings: Submit two 3 inch by 6 inch samples of factory-applied coatings and colors proposed for use for approval prior to coating application.
- C. Certificate of Compliance for Items Coated by Galvanizer: If requested, submit notarized Certificate of Compliance with application for payment for galvanizing, signed by the galvanizer, indicating compliance with requirements of specifications. Include scope of services provided, and quantity and itemized description of items processed.
- D. Certificate of Compliance for Shop Drawing Review by Galvanizer: If requested, submit galvanizer's certification that shop drawings for metal fabrications to receive metal coatings have been reviewed and that fabrications are acceptable to galvanizer for proper application of galvanizing and metal coatings. All drawings shall be signed by the galvanizer to indicate acceptance of design for galvanizing.
- E. Certificate of Compliance of Item Identification by Galvanizer: The galvanizer shall mark all lots of material with a clearly visible tag indicating the name of the galvanizer, the type and weight of the coating, and the applicable ASTM standards. If requested, submit certification of compliance that items have been tagged.

- F. Certificate of Compliance for Shop Application: Galvanizer/applicator shall supply a certificate of compliance with SSPC-QP3 – Certification Standard for Shop Application of Complex Protective Coating Systems.
- G. Substitutions: If substitutions or other products are proposed, submit this specification signed by the firm proposing the other products, indication line-by-line comparison of the proposed substitution or equal product with test results. Substitutions proposed with comparison test results will not be accepted.
- H. Galvanizer's written Quality Control/Quality Assurance manual for hot dip galvanizing and factory applied coating.
- I. Certification from the American Galvanizers Association that Galvanizer has completed all course requirements and is a certified Master Galvanizer.

1.4 QUALITY ASSURANCE

- A. Galvanizer' Qualifications: Engage the services of a qualified galvanizer who has demonstrated a minimum of ten years experience in the successful application of galvanized coatings specified in this specification in the facility where the work is to be performed and who will apply the coatings within the same facility. For surface preparation and shop painting, current SSPC QP-3 certification is required.
- B. Coating Applicator's Qualifications: Galvanizing and factory-applied coatings shall be performed by a company with a minimum of ten years experience in the successful application of hot-dip galvanizing utilizing the dry kettle process.
- C. Pre-Construction Conference for Metal Fabrications to Receive Factory-Applied Metal Coatings: Contractor shall schedule a meeting to be attended by Contractor, Architect, fabricator, and galvanizer. Agenda shall include the following: Project schedule, scope of services, coordination between fabricator and galvanizer, finish of surfaces, application of coatings, color selections, submittals, and approvals.
- D. Coordination between Fabricator and Galvanizer: Prior to fabrication and final submittal of shop drawings to Architect, direct fabricators to submit shop drawings to the galvanizer for all metal fabrications to receive factory-applied metal coatings. Direct galvanizer to review fabricator's shop drawings for suitability of materials for galvanizing and coatings and coordinate any required modifications to fabrications required to be performed by the fabricator.
- E. Environmental Compliance: Coatings shall be certified OTC/VOC compliant and conform to EPA standards and local regulations.
- F. Coating Applicator: For the purpose of establishing a standard of quality and performance, provide factory-applied metal coatings by Duncan Galvanizing, 69 Norman Street, Everett, MA, 02149, telephone 617-389-8440, fax 617-389-2831, www.duncangalvanizing.com.

PART 2 - PRODUCTS

- A. **Hot-Dip Galvanizing:** For steel exposed to the elements, weather or corrosive environments and other steel indicated to be galvanized, provide coating for iron and steel fabrications applied by the hot-dip process. Galvanizing bath shall contain special high grade zinc and other earthly materials.
 - 1. Basis-of-Design **Duragalv**® Hot-dip galvanizing for iron and steel fabrications.
 - 2. Comply with ASTM A 123 for fabricated products and ASTM A 153 for hardware.

3. Provide thickness of galvanizing specified in referenced standards.
4. Fill vent holes after galvanizing, if applicable, and grind smooth.
5. Galvanizing shall be blasted per SSPC SP16 or abraded per SSPC SP2 or SP3 to achieve a 1-3 mil profile.

B. Factory-Applied Primer over Galvanized Steel: Provide factory-applied polyamide epoxy prime coat over hot-dipped galvanized steel.

1. Basis-of-Design: **PRIMERGALV®** by Duncan Galvanizing.
2. Primer shall be certified OTC/VOC compliant at less than 2.8 lbs/gal. and conform to EPA and local requirements.
3. Apply primer within 12 hours after galvanizing at the same galvanizer's plant in a controlled environment meeting applicable environmental regulations and as recommended by the primer coating manufacturer. Primer shall have a one year re-coat window for application of finish coat.
4. Polyamide epoxy primer shall be applied at 4-6 mils DFT and meet or exceed the following performance criteria as stipulated by the coatings manufacturer:
 - a. Abrasion Resistance: ASTM D 4060 (CS17 Wheel, 1,000 grams load) 1 kg load, 200 mg loss.
 - b. Adhesion: ASTM D 4541, 1050 psi.
 - c. Corrosion Weathering: ASTM D 5894, 13 cycles, 4,368 hours, 10 per ASTM D 714 for blistering; 7 per ASTM D 610 for rusting.
 - d. Direct Impact Resistance: ASTM D 2794, 160 in. lbs.
 - e. Flexibility: ASTM D 522, 180 degrees bend, 1 inch mandrel, Passes.
 - f. Pencil Hardness: ASTM D 3363, 3H.
 - g. Moisture Condensation Resistance: ASTM D 4585, 100 degrees F, 2000 hours, Passes no cracking or delamination.
 - h. Dry Heat Resistance: ASTM D 2485, 250 degrees F.
 - i. Accelerated Weathering: QUV- ASTM D 4587 QUV A 5000 Hours: Passes.
 - j. Salt Fog Resistance: ASTM B 117, 5,600 hours No cracking or blisters.

C. Factory-Applied Finish over Primed Steel: Provide factory-applied coating over hot-dip galvanized steel matching approved samples.

1. Basis-of-Design: **Colorgalv Marine® Immersion** by Duncan Galvanizing.
2. Finish coat shall be factory-applied polyamide epoxy color-pigmented finish. Apply finish coating at the galvanizer's plant, in a controlled environment meeting applicable environmental regulations and as recommended by the finish coating manufacturer.
3. Coating shall be certified OTC/VOC compliant and conform to applicable regulations and EPA standards.
4. Apply the galvanizing and coating within the same facility and provide single-source responsibility for galvanizing, priming and finish coating.
5. Clean galvanized surface to create an acceptable profile for coatings. Galvanizer shall certify that performance will be met and coating will be applied within 12 hours of galvanizing or blasting at the galvanizer's plant.
6. Finish coat shall meet or exceed the following performance criteria:
 - a. Abrasion Resistance: ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load, 84 mg loss
 - b. Adhesion: ASTM D4541 1,000 psi
 - c. Direct Impact Resistance: ASTM D2794- 30 in lb
 - d. Dry Heat Resistance: ASTM D2485 250 deg F
 - e. Flexibility: ASTM D522, 180 deg bend, 3/4" mandrel- Passes
 - f. Humidity Resistance: ASTM D4585- No blistering, cracking or rusting

D. Warranty: Provide galvanizer's standard warranty that materials will be free from 10 percent or more visible rust for 20 years.

PART 3 - EXECUTION

3.1 APPLICATION OF FACTORY-APPLIED METAL COATINGS

- A. **Galvanizing Application:** Galvanize materials in accordance with specified standards and this specification. Galvanizing shall provide an acceptable substrate for applied coatings. The dry kettle process shall be used to eliminate any flux inclusions on the surface of the galvanized material.
- B. **Prior to galvanizing,** the steel shall be immersed in a pre-flux solution (zinc ammonium chloride). The pre-flux tank must be 12 to 14 Baumé density and contain less than 0.4 percent iron. Use of the wet kettle process is not acceptable. To provide the galvanized surface required, the following procedures shall be implemented:
1. A monitoring recorder shall be utilized and inspected regularly to observe any variances in the galvanizing bath temperature.
 2. The pickling tanks shall contain hydrochloric acid with an iron content less than 8 percent and zinc content less than 3 percent. Titrations shall be taken weekly at a minimum.
 3. All chemicals and zinc shall be tested at least once a week to determine compliance with ASTM standards. All testing shall be done using atomic absorption spectrometry or x-ray fluorescence (XRF) equipment at a lab in the galvanizing plant.
- C. **.Finish coatings** shall be applied under the following conditions.
1. Minimum air temperature shall be 65 degrees F. Surface temperature of steel shall be 60 degrees to 95 degrees F and, in any event, be 5 degrees F higher than the dew point. Humidity shall be 85 percent maximum.
 2. The use of iron or steel shot and sand and aluminum oxide grit as a blast medium, and power wire brushes are not permitted.
 3. Surface of substrate shall be dry and free from dust, dirt, oil, grease or other contaminants. Coating and cure facility shall be maintained free of airborne dust and dirt until coatings are completely cured.

3.2 INSTALLATION

- A. **Installation:** Comply with fabricator's and galvanizer's requirements for installation of materials and fabrications, including use of nylon slings or padded cables for handling factory-coated materials.
- B. **Touch-Up and Repair:** For damaged and field-welded metal coated surfaces, clean welds, bolted connections and abraded areas.
1. For galvanized surfaces, apply organic zinc repair paint complying with requirements of ASTM A 780, modified to 95 percent zinc in dry film. Galvanizing repair paint shall have 85 percent zinc by weight. ZiRP by Duncan Galvanizing or a Zinc Rich Organic coating may be used. Thickness of applied galvanizing repair paint shall be not less than coating thickness required by ASTM A 123 or A 153 as applicable. Touch-up of galvanized surfaces with silver paint, brite paint, or aluminum paints is not acceptable.
 2. For factory-applied finish coatings, field-touch-up shall be performed by factory approved personnel for warranties to apply. Touch-up shall be such that repair is not visible from a distance of 6 feet. If non factory-approved technicians are used for field touch-up, no warranties shall exist.
 3. A touch-up repair kit or touchup instructions shall be provided to the Owner for each type of factory-applied finish.

END OF SECTION