

Gasket Type	Melting Point
EPDM	150°
White EPDM lid	200°
Santoprene	250°
White Silicone, food grade	400°
Viton lid	450°

Notes:

* Fusible Vents have a melting point of 250°

** The information above is meant as a guide ONLY! Applications may vary. Metano does not warrant (neither expressed nor implied) that the information in these above is accurate or complete or that any material is suitable for any purpose.