

BMC 605LS

Bulk Molding Compound

PRODUCT DESCRIPTION

Low cost glass fiber reinforced Polyester BMC suitable for circuit breakers, transformer bobbins and motor end bells.

GENERAL

Material Status	• Commercial: Active		
Availability	• North America • Asia Pacific	• Europe • South America	
Filler/Reinforcement	• Glass Fiber and mineral filler		
Features	• Medium impact strength • UL Recognized—File E69414	• Excellent electrical properties • UL94-V0 @ 1.8 mm	• Low shrink
Processing Method	• This BMC product is generally intended to be compression, injection or transfer molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1,000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Can be supplied as logs, slugs or bulk forms.		
Resin	• Unsaturated Polyester Composite		

PHYSICAL	Typical	Unit	Test Method
Density	1.88-1.95	g/cm ³	ASTM D792
Mold Shrinkage (RT mold/RT part)	0.001-0.0022	in/in	ASTM D955
Water Absorption, 24 hrs, 23°C	0.14	%	ASTM D570
Hardness, Barcol	40-50	Barcol Units	ASTM D2583
Poisson's Ratio	0.36		ASTM D638

MECHANICAL (As molded)	Typical	Unit	Test Method
Tensile Strength	6,000-8,000 (41-55)	psi (MPa)	ASTM D638
Flexural Strength	16,000-20,000 (110-138)	psi (MPa)	ASTM D790
Compressive Strength	24,000-28,000 (165-193)	psi (MPa)	ASTM D695

BMC 605LS

Bulk Molding Compound

IMPACT	Typical	Unit	Test Method
Izod Notched Impact Strength	2.0-6.0 (105-320)	ft-lb/in (J/m)	ASTM D256
THERMAL	Typical	Unit	Test Method
Heat Deflection Temperature	500+ (260+)	°F (°C)	ASTM D648
UL RTI, Electrical	266 (130)	°F (°C)	UL 746B
UL RTI, Mechanical with Impact	266 (130)	°F (°C)	UL 746B
UL RTI, Mechanical without Impact	266 (130)	°F (°C)	UL 746B
FLAMMABILITY	Typical	Unit	Test Method
Flammability	Pass 0.07 (1.8)	in (mm)	UL94 V-0
ELECTRICAL	Typical	Unit	Test Method
Dielectric Strength	350 (13.8)	Volts/mil (kV/mm)	ASTM D149
Arc Track Resistance	190+	seconds	ASTM D495
Comparative Tracking Index	600+	volts	ASTM D2303

UL File Number E69414



For additional information, please contact:

A. Schulman Inc., Engineered Composites
 1600 Powis Ct, West Chicago, IL 60185
 p: 630-377-1065
 f: 630-377-7395
www.aschulman.com

The information and recommendations contained in this document are based upon data collected by A. Schulman and are believed to be reliable; however, because A. Schulman cannot anticipate or control the many different conditions under which this information and/or product may be used, no representation is made and no warranty is given of any kind, express or implied, for completeness, accuracy, availability, suitability, usefulness, commercial value, or non-violation of intellectual property rights of information, recommendation, and products and services directly or indirectly provided. A. Schulman assumes no responsibility for the results of the use of products and processes described herein and expressly disclaims the implied warranties of merchantability and fitness for a particular use.