

Premi-Glas[®] 3101-22

Bulk Molding Compound

PRODUCT DESCRIPTION

Glass fiber reinforced Polyester BMC suitable for electrical circuit breakers, switchgear, and other applications where fire retardance is required

GENERAL

Material Status	• Commercial: Active		
Availability	• North America • Asia Pacific	• Europe • South America	
Filler/Reinforcement	• Glass Fiber and mineral filler		
Features	• Non-Halogen FR technology • UL Recognized—File E69414	• Good dimensional stability • UL94-V-0 @ 1.6 mm	• Excellent electrical properties
Processing Method	• This BMC product is generally intended to be compression or injection molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1,000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Extrusions available.		
Resin	• Unsaturated Polyester Composite		

PHYSICAL	Typical	Unit	Test Method
Density	1.80-1.95	g/cm ³	ASTM D792
Mold Shrinkage (RT mold/RT part)	0.0015-0.0030	in/in	ASTM D955
CLTE, X-Y plane	25	ppm/°C	ASTM E831
CLTE, Z plane	35	ppm/°C	ASTM E831
Poisson's Ratio	0.36		ASTM D638

MECHANICAL (As cut)	Typical	Unit	Test Method
Tensile Modulus	1.92 x 10 ⁶ (13.2)	psi (GPa)	ASTM D638
Tensile Strength	4,800 (33)	psi (MPa)	ASTM D638
Flexural Modulus (RT)	1.6 x 10 ⁶ (11.0)	psi (GPa)	ASTM D790
Flexural Strength	17,000 (117)	psi (MPa)	ASTM D790

Premi-Glas® 3101-22

Bulk Molding Compound

IMPACT	Typical	Unit	Test Method
Izod Notched Impact Strength	9 (480)	ft-lb/in (J/m)	ASTM D256
Unnotched Impact Strength	11 (585)	ft-lb/in (J/m)	ASTM D4812

THERMAL	Typical	Unit	Test Method
Heat Deflection Temperature, 264 psi	400+ (200+)	°F (°C)	ASTM D792
Thermal Conductivity, 25°C	0.30	W/m**K	ASTM E1461
UL RTI, Electrical	266 (130)	°C	UL 746C
UL RTI, Mechanical with Impact	266 (130)	°C	UL 746C
UL RTI, Mechanical without Impact	266 (130)	°C	UL 746C

FLAMMABILITY	Typical	Unit	Test Method
Flammability	Pass 0.063 (1.6)	in (mm)	UL94-V0
Flammability	Pass 0.102 (2.6)	in (mm)	UL94-5V

ELECTRICAL	Typical	Unit	Test Method
Dielectric Strength	450 (18)	Volts/mil (kV/mm)	ASTM D149
Arc Track Resistance	210+	seconds	ASTM D495

UL File Number E69414



For additional information, please contact:

A. Schulman Inc., Engineered Composites
 1600 Powis Ct, West Chicago, IL 60185
 p: 630-377-1065
 f: 630-377-7395
www.aschulman.com

The information and recommendations contained in this document are based upon data collected by A. Schulman and are believed to be reliable; however, because A. Schulman cannot anticipate or control the many different conditions under which this information and/or product may be used, no representation is made and no warranty is given of any kind, express or implied, for completeness, accuracy, availability, suitability, usefulness, commercial value, or non-violation of intellectual property rights of information, recommendation, and products and services directly or indirectly provided. A. Schulman assumes no responsibility for the results of the use of products and processes described herein and expressly disclaims the implied warranties of merchantability and fitness for a particular use.