

# Quantum Lytex<sup>®</sup> 9063 BK-E

## Sheet Molding Compound

### PRODUCT DESCRIPTION

E-glass reinforced epoxy molding compound

#### GENERAL

<b>Material Status</b>	• Commercial: Active		
<b>Availability</b>	• North America	• Europe	• Asia Pacific
<b>Filler/Reinforcement</b>	• E-glass Fiber	• Nominal 63% w/w	• Nominal 1/2" (12.5 mm) Length
<b>Features</b>	• Fatigue resistance • High strength	• High stiffness • Shelf Life 6 months @ 10°F or below	• Black or Natural Color
<b>Processing Method</b>	• <b>Lytex<sup>®</sup> 9063 BK-E</b> can be molded at temperatures in the range of 280-330°F, with 310°F suggested as a starting point. Cure times will be dependent on molding temperature and part thickness and will typically be 10-15 minutes. Detailed molding suggestions are available on request. Cool molded parts at ambient temperature. A cooling fixture may be needed depending on part thickness and geometry. Matched metal die molds.		
<b>Resin</b>	• Epoxy Composite		

PHYSICAL	Typical	Unit	Test Method
Density	1.82	g/cm <sup>3</sup>	ASTM D792
Shrinkage	<0.001	in/in	cold mold to cold part
CLTE, X-Y plane	14	ppm/°C	ASTM E831
CLTE, Z plane	58	ppm/°C	ASTM E831
Poisson's Ratio	0.33		ASTM D638

MECHANICAL (Machined)	Typical	Unit	Test Method
Tensile Modulus	2.6E+6 (18,000)	psi (MPa)	ASTM D3039
Tensile Stress (Break)	28,000 (193)	psi (MPa)	ASTM D3039
Flexural Modulus	2.6E+6 (18,000)	psi (MPa)	ASTM D790
Flexural Stress (Break)	59,000 (407)	psi (MPa)	ASTM D790
Short Beam Shear	6,500 (44.8)	psi (MPa)	ASTM D2344

Machined Properties are determined using specimen machined from molded 12"x12" panels with 80% mold coverage, 1000 psi pressure, 280-300°F mold temperature for 3-5 minutes

The information and recommendations contained in this document are based upon data collected by A. Schulman and are believed to be reliable; however, because A. Schulman cannot anticipate or control the many different conditions under which this information and/or product may be used, no representation is made and no warranty is given of any kind, express or implied, for completeness, accuracy, availability, suitability, usefulness, commercial value, or non-violation of intellectual property rights of information, recommendation, and products and services directly or indirectly provided. A. Schulman assumes no responsibility for the results of the use of products and processes described herein and expressly disclaims the implied warranties of merchantability and fitness for a particular use.

# Quantum Lytex<sup>®</sup> 9063 BK-E

## Sheet Molding Compound

<b>MECHANICAL (As molded)</b>	<b>Typical</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	3.3E+6 (22,800)	psi (MPa)	ASTM D638
Tensile Strength	35,000 (241)	psi (MPa)	ASTM D638
Flexural Modulus (RT)	2.6E+6 (18,000)	psi (MPa)	ASTM D790
Flexural Strength	66,000 (455)	psi (MPa)	ASTM D790
<b>IMPACT</b>			
Izod Notched Impact Strength	35 (1869)	ft-lb/in (J/m)	ASTM D256
<b>THERMAL</b>			
Glass Transition T <sub>i</sub> , TanDelta	165	°C	ASTM D7028
Glass Transition T <sub>g</sub> , Storage Modulus	120	°C	ASTM D7028
Heat Deflection Temperature	>575 (300)	°F (°C)	ASTM D648
<b>ELECTRICAL</b>			
Dielectric Strength	450	Volts/mil (kV/mm)	ASTM D149
Volume Resistivity	1.1E+16	ohm-cm	ASTM D257
Dissipation Factor	0.0049	100 Hz	ASTM D150
Dielectric Constant	4.3	100 Hz	ASTM D150

For additional information, please contact:

**A. Schulman Inc., Engineered Composites**  
**Quantum Composites, Inc.**  
 1310 South Valley Center Drive  
 Bay City, MI 48604  
 p: 989-922-3863  
 f: 989-922-3915  
[www.aschulman.com](http://www.aschulman.com)

The information and recommendations contained in this document are based upon data collected by A. Schulman and are believed to be reliable; however, because A. Schulman cannot anticipate or control the many different conditions under which this information and/or product may be used, no representation is made and no warranty is given of any kind, express or implied, for completeness, accuracy, availability, suitability, usefulness, commercial value, or non-violation of intellectual property rights of information, recommendation, and products and services directly or indirectly provided. A. Schulman assumes no responsibility for the results of the use of products and processes described herein and expressly disclaims the implied warranties of merchantability and fitness for a particular use.