

Premi-Glas 2550[®] B-AM-CR-SX

Sheet Molding Compound

PRODUCT DESCRIPTION

Glass fiber reinforced Polyester SMC suitable for electrical, flame retardant, and HVAC applications where stringent flame spread and smoke generation criteria are required in combination with anti-microbial properties.

GENERAL

Material Status	• Commercial: Active		
Availability	• North America	• South America	
Filler/Reinforcement	• Glass Fiber and mineral filler		
Features	<ul style="list-style-type: none"> • Proprietary Anti-Microbial agents. • (f1) - Suitable for outdoor use • Meets Steiner Tunnel < 25 Flame Spread Index and < 50 Smoke Index • UL Recognized—File E69414 • UL94-V0/5V @ 1.5 mm 		
Processing Method	• This SMC product is generally intended to be compression molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1,000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process.		
Resin	• Unsaturated Polyester Composite		

PHYSICAL	Typical	Unit	Test Method
Density	2.00	g/cm ³	ASTM D792
Mold Shrinkage (RT mold/RT part)	0.00025-0.0015	in/in	ASTM D955
CLTE, X-Y plane	23	ppm/°C	ASTM E831
CLTE, Z plane	35	ppm/°C	ASTM E831
Poisson's Ratio	0.21		ASTM D638

MECHANICAL (As cut)	Typical	Unit	Test Method
Tensile Modulus	1.9 x 10 ⁶ (13)	psi (GPa)	ASTM D638
Tensile Strength	10,000 (70)	psi (MPa)	ASTM D638
Flexural Modulus (RT)	1.38 x 10 ⁶ (9.5)	psi (GPa)	ASTM D790
Flexural Strength	24,000 (165)	psi (MPa)	ASTM D790

Premi-Glas 2550® B-AM-CR-SX

Sheet Molding Compound

IMPACT	Typical	Unit	Test Method
Izod Notched Impact Strength	13 (700)	ft-lb/in (J/m)	ASTM D256
Unnotched Impact Strength	18.5 (1000)	ft-lb/in (J/m)	ASTM D4812

THERMAL	Typical	Unit	Test Method
Thermal Conductivity, 25°C	1.3	W/m-°K	ASTM E1461
UL RTI, Electrical	221 (105)	°F (°C)	UL 746C
UL RTI, Mechanical with Impact	266 (130)	°F (°C)	UL 746C
UL RTI, Mechanical without Impact	266 (130)	°F (°C)	UL 746C

FLAMMABILITY	Typical	Unit	Test Method
Flammability	Pass 0.060 (1.5)	in (mm)	UL94 V-0 & 5V
Flame Spread Index	5		UL723 Steiner Tunnel
Smoke Developed Index	20-50		UL723 Steiner Tunnel

UL File Number E69414



For additional information, please contact:

A. Schulman Inc., Engineered Composites
 3365 East Center St, Conneaut, Ohio 44030
 p: 440-224-2181
 f: 440-224-2766
www.aschulman.com

The information and recommendations contained in this document are based upon data collected by A. Schulman and are believed to be reliable; however, because A. Schulman cannot anticipate or control the many different conditions under which this information and/or product may be used, no representation is made and no warranty is given of any kind, express or implied, for completeness, accuracy, availability, suitability, usefulness, commercial value, or non-violation of intellectual property rights of information, recommendation, and products and services directly or indirectly provided. A. Schulman assumes no responsibility for the results of the use of products and processes described herein and expressly disclaims the implied warranties of merchantability and fitness for a particular use.