



Safety & Security Window Films

Performance Results*:

Visible Light Transmitted	27%
Total Solar Energy Rejected	63%
UV Light Rejected	99%
Glare Reduction	69%
Visible Light Reflected Int.	12%
Visible Light Reflected Ext.	23%
Solar Heat Reduction	54%



Ultra Night Vision S25

Scan for ratings
and reviews



Enhancing safety
as only 3M can



S25NVAR400


Ultra Night Vision S25 Benefits:

- 3M proprietary technology utilizes many microlayers in a 5 mil film to provide strength and tear resistance compared to standard PET films
- Improves personal, property and asset protection from hurricanes, blasts and earthquakes
- Comprehensive 3M manufacturer's warranty
- Reduces fading and helps to protect furnishings
- A warm natural hue invites warmth and beauty to any room
- New 3M nano-technology enhances color stability
- Deters smash and grab burglaries
- Increases personal safety from flying glass
- High heat rejection provides energy savings and improved comfort
- Reduces glare and eye discomfort
- Meets Safety Glazing Standard CPSC 16 CFR Category II (400 ft./lb.) and ANSI Z97.1, and passes Intensified Weathering Test

*Performance data generated for a typical film on 6mm glass using applicable industry test methods and standards.



The Skin Cancer Foundation recommends this 3M Window Film product as an effective UV protectant.





Ultra Night Vision S25

Scan for ratings
and reviews



Enhancing safety
as only 3M can



Glass Type (All 1/4")	Single Pane Clear	Single Pane Tinted	Double Pane Clear	Double Pane Tinted
Visible Light Transmitted	27%	16%	25%	15%
Visible Light Reflected Int.	12%	12%	13%	13%
Visible Light Reflected Ext.	23%	11%	27%	13%
Total Solar Energy Rejected	63%	65%	53%	64%
UV Light Rejected	99%	99%	99%	99%
Glare Reduction	69%	69%	69%	69%
Solar Heat Gain Coefficient	0.38	0.35	0.47	0.36
Luminous Efficacy	0.7	0.5	0.5	0.4
U Value	0.97	0.97	0.46	0.46
Solar Heat Reduction	54%	31%	33%	29%



3M Renewable Energy Division

3M Center, Building 235-2S-27
St. Paul, MN 55144-1000

Printed in U.S.A. © 3M 2011 70-0709-0183-3 (111.65)ii

No UV Protection or Abrasion Coating has been applied to this sample card.