





Benefits and selection criteria

- Helps hold shattered glass together should a break occur
- Helps slow down entry through glass
- Pressure-sensitive adhesive has a low visual distortion that provides optical clarity
- Most often used to help hold shattered glass in place in the event of a windstorm or blast
- Also can be used for added protection during human impact, an earthquake or in the event of spontaneous tempered glass breakage
- Provides extreme reduction of heat and glare with daytime privacy
- Shields >99% of UV radiation, helping to reduce fading of valuables, fabrics and furnishings**
- Please see LLumar.com for recommendations and test results for specific glass and frame types



ΕΛSTΜΛΝ

LLumar.com

*Certain restrictions apply, see an authorized dealer for warranty details. **Films do not eliminate fading - they reduce it. UV rays and heat are contributing factors to fading, but other factors exist. For further information, see LLumar.com/download-library. © 2016 Eastman Chemical Company. LLumar® and the LLumar® logo are trademarks of Eastman Chemical Company or one of its wholly owned subsidiaries. As used herein, ® denotes registered trademark status in the U.S. only. Printed in U.S.A. (06/16) L1381



SOLAR SAFETY SERIES | R20 SR PS8 (Silver)





Performance Data	% Total Solar Transmittance	% Total Solar Reflectance	% Total Solar Absorptance	% Visible Light Transmittance	% Visible Reflectance (exterior)	% Visible Reflectance (interior)	Winter U-value	Shading Coefficient	% Ultraviolet Ray Protection (wavelengths 300-380nm)	Emissivity	Solar Heat Gain Coefficient	% Total Solar Energy Rejected	Light-to-Solar Heat Gain Ratio (LSG)	% Summer Solar Heat Gain Reduction	% Winter Heat Loss Reduction	% Glare Reduction
Clear Glass 1/8" (3mm) single pane	83	8	9	90	8	8	1.03	1.00	29	0.84	0.86	14	1.05	-	-	-
R20 SR PS8 1/8" (3mm) single pane	11	59	30	15	64	64	1.06	0.24	>99	0.87	0.20	80	0.75	77	-2	83
Physical Properties	Film Thickness (inches)	(becom)	Appearance Film Structure			Tensile Strength (constructed)	(constructed) (constructed) Tensile Strength		Break Strength (peak load)		Break Strength (average load)	Elongation at Break		Peel Strength	Peel Strength	
R20 SR PS8	0.00		Silver eflective	M	ulti	32,473	3 32	2,000	269		260	>1()0% :	>2720 (>	6) :	164

The solar performance data reported for LLumar architectural window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement. All safety and performance data has been measured in accordance with ASTM, ASHRAE, AIMCAL and ANSI standards using NFRC methodology with Lawrence Berkeley National Lab's WINDOW Fenestration Analysis Software. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.