

纱管纸外控标准
(CORE BOARD TECHNICAL SPECIFICATIONS)

纸板等级	基重 (g/m2)	厚度 (um)	紧度 (g/cm3)	下纸环压MD (N.m/g)	层间 (J/m2)	含水量 (%)	吸水度60s (Gr/m2)
Grade	Basis Wt.	Caliper	Density	Pope Reel Ring Crush	Scott Ply-Bond	Moisture	Cobb Size
P200	360	500	0.70-0.76	≥11	≥220	7.0±2.0	100-350
	>360	>500		≥11.5			
CB	≥300	≥410	0.70-0.76	≥12	≥240	7.0±2.0	100-350
P260	360	500	0.70-0.76	≥12.5	≥260	7.0±2.0	100-350
	>360	>500		≥13			
P300	360	500	0.70-0.76	≥15.5	≥300	7.0±2.0	100-350
	>360	>500		≥16.5			
P360	360	480	0.70-0.78	≥17	≥360	7.0±2.0	100-350
	>360	>480		≥18			
P400	360	480	0.70-0.78	≥19	≥400	7.0±2.0	100-350
	>360	>480		≥20			
P460	360	480	0.70-0.78	115 - 145	≥460	7.0±2.0	100-350
	>360	>480		125 - 160			
P500	360	480	0.70-0.78	135 - 170	≥500	7.0±2.0	100-350
	>360	>480		145 - 180			
P600	>360	>470	0.70-0.79	22	≥600	7.0±2.0	80-250
PTD-7A	>360	>460	0.70-0.79	24	≥800	7.0±2.0	40-120

备注：

1.厚度/Caliper: ±20um

2.基重/Basis weight: ±4%

3.We can adjust water value, moisture, etx. Per customer demands. 吸水值、紧度、水分及其它情况，根据客户实际要求调整。