

Analytical Reference Materials International



Certificate of Analysis Certified Reference Material

Grade: **AISI 303Se / UNS S30323**
Part Number (Q.A. NO.): **IARM 253B**

Certificate Date: **07/19/2017**

Certificate No.: **253B-07192017-IARM-F**

Revision Date: **10/11/2017**

Interpretation of Data

- Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
- Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
- The "Inter laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
Chips are not certified for Oxygen analysis.
- The **"±Estimated Uncertainty"** is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u>	<u>Antimony</u>	<u>Arsenic</u>	<u>Boron</u>	<u>Calcium</u>	<u>Carbon</u>	<u>Cerium</u>	<u>Chromium</u>	<u>Cobalt</u>
0.004 (0.002)	(0.0018)	0.0052 (0.0006)	0.0007 (0.0003)	(0.0006)	0.051 (0.001)	(<0.001)	17.64 (0.03)	0.145 (0.004)
<u>Copper</u>	<u>Lead</u>	<u>Magnesium</u>	<u>Manganese</u>	<u>Molybdenum</u>	<u>Nickel</u>	<u>Niobium</u>	<u>Nitrogen</u>	<u>Oxygen</u>
0.44 (0.01)	(0.0002)	(0.0006)	1.61 (0.02)	0.59 (0.01)	9.11 (0.04)	0.021 (0.001)	0.031 (0.002)	0.007 (0.001)
<u>Phosphorus</u>	<u>Selenium</u>	<u>Silicon</u>	<u>Sulfur</u>	<u>Tantalum</u>	<u>Tin</u>	<u>Titanium</u>	<u>Tungsten</u>	<u>Vanadium</u>
0.13 (0.01)	0.13 (0.01)	0.46 (0.02)	0.011 (0.001)	(0.003)	0.012 (0.003)	0.0027 (0.0009)	0.05 (0.01)	0.092 (0.003)
<u>Zinc</u>	<u>Zirconium</u>							
(<0.002)	(<0.008)							

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

AADFW, Inc. - Euless, TX	Exova Burlington Lab - Burlington, ON
Anderson Laboratories, Inc. - Greendale, WI	Keywell Metals LLC - Falconer, NY
Certified Alloy Products - Long Beach, CA	Laboratory Testing, Inc. - Hatfield, PA
Cronimet Specialty Metals USA, Inc - Wheatland, PA	Special Metals IncoTest - Hereford, UK
Crucible Industries - Syracuse, NY	SPECTRO Analytical Instruments Inc. - Mahwah, NJ
Exova - Gary, IN	

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are:

ALPHA AR1653	BCS 334	BS 80E	ECRM 287/1	IARM 21B	LECO 501-502	NIST 1249	NIST 3165A	NIST 899
ALPHA AR1656	BCS 345	BS 80F	HAS 317B	IARM 23C	LECO 501-673	NIST 160A	NIST 339	
ALPHA AR654	BCS 346	BS 812F	IARM 16B	IARM 241A	LECO 502-494	NIST 3109A	NIST 3482	
ALPHA AR659	BCS 351/1	BS 81E	IARM 1B	IARM 253A	LECO 502-991	NIST 3131A	NIST 361	
ALPHA AR881	BCS 457/2	BS 84J	IARM 1C	IARM 2C	MBH 303	NIST 3149	NIST 73C	
ALPHA AR882	BCS 462/2	CARTECH 303SE	IARM 1D	IARM 319A	NIST 101G	NIST 3155	NIST 897	
BAS 466	BS 80C	ECRM 281/1	IARM 212B	IARM 4B	NIST 1154	NIST 3163	NIST 898	

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

276 Abby Road • Manchester, NH • Telephone (603) 935-4100 • FAX (603) 935-4101

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 10/11/2017.

253B	Al	Sb	As	B	Ca	C	Ce	Cr	Co	Cu	Pb	Mg	Mn	Mo	Ni	Nb
1	0.0012	0.0014	0.0043	0.00028	0.00046	0.048	<0.0001	17.53	0.1370	0.41	0.00003	0.0001	1.5307	0.5453	8.986	0.0184
2	0.0014	0.0015	0.0049	0.0003	0.0008	0.049		17.606	0.1388	0.428	0.00005	0.0002	1.57	0.5731	9.0633	0.0184
3	0.0014	0.0016	0.0052	0.0004	<0.0001	0.049		17.61	0.139	0.43	0.0001	0.0015	1.588	0.580	9.066	0.020
4	0.0026	0.0016	0.0052	0.0006		0.0496		17.61	0.144	0.435	0.0003		1.60	0.582	9.067	0.020
5	0.0028	0.0030	0.0057	0.0006		0.0499		17.618	0.1444	0.437	<0.00068		1.608	0.5888	9.07	0.021
6	0.0042		0.006	0.0009		0.0504		17.633	0.1450	0.4380			1.614	0.595	9.10	0.021
7	0.0057			0.0009		0.0506		17.64	0.145	0.4408			1.6147	0.595	9.103	0.0223
8	0.0061			0.00092		0.0508		17.6674	0.146	0.441			1.62	0.600	9.1159	0.0227
9	0.012			0.0018		0.051		17.6775	0.146	0.45			1.6224	0.60	9.1178	0.023
10						0.05165		17.693	0.15	0.4515			1.624	0.6039	9.14	0.0239
11						0.052		17.70	0.151	0.4677			1.6275	0.609	9.155	0.0251
12						0.0528		17.71	0.157				1.6616	0.613	9.21	
13						0.0542							1.662	0.6409	9.223	
14																
15																
Mean	0.004	0.0018	0.0052	0.0007	0.0006	0.051		17.64	0.145	0.44	0.0002	0.0006	1.61	0.59	9.11	0.021
STDV.	0.003	0.0007	0.0006	0.0005	0.0002	0.002		0.05	0.006	0.01	0.0003	0.0008	0.03	0.02	0.06	0.002
Certified	0.004	(0.0018)	0.0052	0.0007	(0.0006)	0.051	(<0.001)	17.64	0.145	0.44	(0.0002)	(0.0006)	1.61	0.59	9.11	0.021
95% C.I.	0.002		0.0006	0.0003		0.001		0.03	0.004	0.01			0.02	0.01	0.04	0.001
Methods	O,I,A	O,IM,H,A	O,IM,H,A	O,I	O,I	O,C	IM	X,O,I	X,O,I	X,O,I	O,IM,H	I,H	X,O,I	X,O,I	X,O,I	X,O,I

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, IM=ICP-MS, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

253B	N	O	P	Se	Si	S	Ta	Sn	Ti	W	V	Zn	Zr
1	0.027	0.0051	0.082	0.1105	0.402	0.006	0.001	0.0069	0.001	0.0134	0.0867	0.00002	0.0002
2	0.028	0.0054	0.1040	0.114	0.4348	0.0072	0.0052	0.0094	0.001	0.021	0.0878	0.0002	0.0007
3	0.0285	0.006	0.1212	0.124	0.4370	0.0095	<0.0001	0.010	0.0017	0.04	0.0889	0.0018	0.001
4	0.0298	0.0069	0.1227	0.1280	0.4410	0.0103	<0.0010	0.0101	0.0018	0.05	0.089	<0.0001	0.001
5	0.030	0.007	0.131	0.132	0.45	0.0106	<0.005	0.011	0.0026	0.051	0.0898		0.001
6	0.0305	0.0071	0.135	0.133	0.468	0.011	<0.005	0.0122	0.0028	0.0512	0.0910		0.0073
7	0.0310	0.0097	0.1360	0.1403	0.472	0.0112	<0.01	0.0126	0.0028	0.052	0.0912		
8	0.031		0.1383	0.1505	0.473	0.0115		0.013	0.004	0.055	0.092		
9	0.0328		0.142	0.1506	0.483	0.0116		0.0141	0.0045	0.0557	0.092		
10	0.0354		0.142	0.160	0.485	0.012		0.0218	0.0046	0.0583	0.092		
11	0.0398		0.1450		0.4859	0.0122				0.066	0.0972		
12			0.1543		0.4865	0.0135					0.102		
13			0.157		0.487	0.0137							
14													
15													
Mean	0.031	0.007	0.13	0.13	0.46	0.011	0.003	0.012	0.0027	0.05	0.092	0.001	0.002
STDV.	0.004	0.002	0.02	0.02	0.03	0.002	0.003	0.004	0.0013	0.02	0.004	0.001	0.003
Certified	0.031	0.007	0.13	0.13	0.46	0.011	(0.003)	0.012	0.0027	0.05	0.092	(<0.002)	(<0.008)
95% C.I.	0.002	0.001	0.01	0.01	0.02	0.001		0.003	0.0009	0.01	0.003		
Methods	O,F	O,F	X,O,I	X,O,I	X,O,I	O,C	X,O,IM,I	O,IM,I,A	X,O,I	X,O,I	X,O,I	IM,H,A	X,O,IM

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, IM=ICP-MS, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1992 list the following:

Certifying Body: Any technically competent body (organization or firm, public or private) that issues a reference material certificate, which provides the information, detailed in ISO Guide 31. The only generally accepted certifying body in the United States for primary standards - Standard Reference Materials (SRM) is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD. All other certifying bodies in the United States produce Reference Materials (RM) or Certified Reference Materials (CRM).

Reference Material (RM): Material or substance one or more of whose property values are sufficiently homogeneous and well established to be used for the calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): Reference material, accompanied by a certificate, one or more of whose property values are certified by a procedure, which establishes its traceability to an accurate realization of the unit in which the property values are expressed, and for which each certified value is accompanied by an uncertainty at a stated level of confidence.


Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion and OE instrument procedures.

Expiration of Certification: The certification of this IARM is valid indefinitely, within the uncertainty specified, provided the IARM is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the IARM is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.

Instructions for Use: The test surface is the side opposite to the labeled surface, which includes the IARM number. The entire thickness of the unit is certified. However, the user is cautioned not to measure disks less than 2 mm thick when using X-ray fluorescence spectrometry. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing as these processes may contaminate the surface. When not in use, the material should be stored in a cool, dry location. This material was tested using both the solid disks and chips prepared from the disks. The certified values are considered representative of the overall average composition of the material. Chips are not to be used for Oxygen analysis.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.


 David Coler, General Manager
 Analytical Reference Materials International



Certificate No.: 253B-07192017-IARM-F
 Certificate Date: 7/19/2017
 Revision Date: 10/11/2017