



ARMI

ISO Certified · 9001 · 17025 · 17043 · 17034

# Certificate of Analysis

## IARM AI6061-18

Aluminum AA6061 / UNS A96061

### Certified Reference Material

Certified Values listed in wt.% with associated uncertainties

<b>Cr</b>	<b>0.103 ± 0.002</b>	<b>Cu</b>	<b>0.271 ± 0.005</b>	<b>Fe</b>	<b>0.310 ± 0.006</b>	<b>Mg</b>	<b>0.88 ± 0.01</b>
<b>Mn</b>	<b>0.105 ± 0.003</b>	<b>Ni</b>	<b>0.0081 ± 0.0007</b>	<b>Pb</b>	<b>0.0023 ± 0.0009</b>	<b>Si</b>	<b>0.67 ± 0.04</b>
<b>Sn</b>	<b>0.005 ± 0.003</b>	<b>Ti</b>	<b>0.016 ± 0.001</b>	<b>V</b>	<b>0.013 ± 0.002</b>	<b>Zn</b>	<b>0.023 ± 0.002</b>
<b>Zr</b>	<b>0.0022 ± 0.0005</b>						

Indicative Values listed in ppm

Ag (<20)	Al (97.3%)	As (<50)	B (8)	Be (<1)	Bi (<70)	C (<200)
Ca (20)	Cd (1)	Co (2)	Ga (122)	H (<10)	Hf (<10)	In (<30)
Mo (<10)	N (<10)	Na (<10)	Nb (<10)	O (<10)	P (30)	Pd (<10)
S (<10)	Sb (<100)	Se (<50)	Ta (<10)	W (<120)	Y (<10)	

#### Description and Intended Use

This **Certified Reference Material** is covered under the scope of accreditation to **ISO 17034** by LGC Standards - Manchester, NH. As an ISO 17034 certified reference material, appropriate use of this material will fulfill the certified reference material and traceability requirements for use in **ISO 17025** certified laboratories. This CRM may come in the form of a solid disk, chips, or powder. The intended use of this CRM may include, but is not limited to, the calibration of instruments and the validation of analytical methods.

#### Instructions for Use

1. The test surface is on the opposite side of the labeled surface, which includes the material identification. The entire thickness of the unit is certified. However, the user is cautioned not to measure disks less than 2 mm thick when using X-ray fluorescence spectrometry. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing, as these processes may contaminate the surface.
2. The minimum sample size for chips should be individually evaluated based on the analytical technique used; this would typically be greater than 0.1 grams.
3. The material should be stored in a cool, dry location when not in use.
4. Chips are not recommended for gas analysis.

The following data represents all pertinent information reported as it applies to the chemical characterization of this material.

	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Si	Sn	Ti	V	Zn	Zr	Ag	Al	As
1	0.098	0.257	0.29	0.8512	0.099	0.006	0.0017	0.534	0.00253	0.012	0.011	0.017	0.0018	0.0015	96.41	0.0012
2	0.10	0.2597	0.3013	0.873	0.10	0.007	0.002	0.61	0.0029	0.0146	0.011	0.02027	0.00192		97.56	<0.001
3	0.101	0.264	0.303	0.8773	0.1013	0.0072	0.002	0.6327	0.003	0.015	0.011	0.021	0.002		97.597	<0.001
4	0.1027	0.27	0.303	0.879	0.1017	0.0074	0.0021	0.6383	0.003	0.01536	0.0117	0.023	0.0020		97.603	<0.005
5	0.103	0.2706	0.304	0.88	0.1023	0.0076	0.0022	0.6584	0.0032	0.016	0.012	0.0231	0.002			
6	0.103	0.271	0.3101	0.88	0.1045	0.0078	0.004	0.6795	0.0035	0.016	0.01248	0.024	0.0027			
7	0.104	0.2717	0.311	0.88	0.1052	0.008		0.68	0.004	0.016	0.0143	0.02467	0.003			
8	0.104	0.2725	0.312	0.886	0.106	0.008		0.683	0.00768	0.0163	0.0194	0.02495				
9	0.1045	0.275	0.3129	0.895	0.108	0.008		0.705	0.015	0.0168		0.025				
10	0.1053	0.2763	0.3133	0.8976	0.11	0.0087		0.718		0.017		0.025				
11	0.1057	0.278	0.316	0.903	0.111	0.0096		0.726		0.0179		0.025				
12	0.107	0.286	0.322	0.917	0.113	0.01		0.73		0.018		0.0256				
13			0.326			0.0101		0.75		0.0187		0.0258				
14																
Mean	0.103	0.271	0.310	0.88	0.105	0.0081	0.0023	0.67	0.005	0.016	0.013	0.023	0.0022		97.3	
STDV.	0.003	0.008	0.009	0.02	0.005	0.001	0.0008	0.06	0.004	0.002	0.003	0.003	0.0005		0.6	
Certified	<b>0.103</b>	<b>0.271</b>	<b>0.310</b>	<b>0.88</b>	<b>0.105</b>	<b>0.0081</b>	<b>0.0023</b>	<b>0.67</b>	<b>0.005</b>	<b>0.016</b>	<b>0.013</b>	<b>0.023</b>	<b>0.0022</b>	<b>(&lt;0.002)</b>	<b>(97.3)</b>	<b>(&lt;0.005)</b>
U <sub>CRM</sub>	0.002	0.005	0.006	0.01	0.003	0.0007	0.0009	0.04	0.003	0.001	0.002	0.002	0.0005			
Methods	I,IM,O,X	I,IM,O,X	I,IM,O,X	I,O,X	I,IM,O,X	I,IM,O,X	I,IM,O	I,O,X	I,IM,O,X	I,IM,O,X	I,IM,O,X	I,IM,O,X	I,IM,O,X	O	I,O,X	I,IM

	B	Be	Bi	C	Ca	Cd	Co	Ga	H	Hf	In	Mo	N	Na	Nb	O
1	0.00063	0.0001	0.00026	0.01254	0.0007	0.000034	0.000197	0.0115	0.000051	<0.001	0.0028	0.00071	<0.001	0.0008	0.001	0.001
2	0.0007		0.000417	<0.001	0.000767	0.000127	0.0002	0.012	<0.001			<0.001	<0.001		<0.001	<0.001
3	0.00081		0.00672	<0.005	0.0019	<0.0001	0.0002	0.01237				<0.001	<0.001		<0.001	<0.001
4	0.001		<0.0001		0.002	<0.001	<0.001	0.0128				<0.001				
5	<0.001		<0.001		0.006	<0.001	<0.001									
6	<0.001		<0.001		<0.001	<0.001	<0.001									
7	<0.005		<0.005		<0.005	<0.005	<0.005									
Mean	0.0008		0.002		0.002	0.00010	0.000199	0.0122								
STDV.	0.0002		0.004		0.002	0.00007	0.000002	0.0006								
U <sub>CRM</sub>	<b>(0.0008)</b>	<b>(&lt;0.0001)</b>	<b>(&lt;0.007)</b>	<b>(&lt;0.02)</b>	<b>(0.002)</b>	<b>(0.0001)</b>	<b>(0.0002)</b>	<b>(0.0122)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.003)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.001)</b>
Methods	I,IM,O	O	I,IM,O	C	I,IM,O	I,IM,O	I,IM,O	I,O,X	F	IM	O	I,IM	I,F	O	I,IM	F

	P	Pd	S	Sb	Se	Ta	W	Y								
1	0.00044	<0.001	<0.001	0.000054	0.002	<0.001	0.00032	<0.001								
2	0.0015		<0.001	0.00007	<0.001	<0.001	0.001									
3	0.004		<0.001	0.0003	<0.005	<0.001	0.012									
4	0.0043			0.009	<0.005		<0.001									
5	<0.001			<0.001			<0.001									
6	<0.005			<0.001			<0.001									
7	<0.005			<0.005												
Mean	0.003			0.002												
STDV.	0.002			0.004												
U <sub>CRM</sub>	<b>(0.003)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.01)</b>	<b>(&lt;0.005)</b>	<b>(&lt;0.001)</b>	<b>(&lt;0.012)</b>	<b>(&lt;0.001)</b>								
Methods	I,IM,O	IM	C	I,IM,O	I,IM	I,IM	I,IM	IM								

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, IM=ICP-MS, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

### Certification Laboratories

Applied Technical Services, Inc.	Marietta, GA	Connecticut Metallurgical, Inc.	East Hartford, CT
Dirats Laboratories	Westfield, MA	EAG Laboratories, Inc.	Liverpool, NY
Element Materials Technology	Gary, IN	IMR Test Labs	Lansing, NY
Massachusetts Materials Research, Inc.	West Boylston, MA	NSL Analytical Services, Inc.	Cleveland, OH
SGS MSI	Melrose Park, IL	VHG Labs	Manchester, NH

Certification laboratories have demonstrated performance and traceability by utilizing test methods under the scope of ISO 17025 or have shown competence through a proficiency testing program. Some of the specific CRMs and SRMs used in the analysis of the material covered by this certificate are:

NBS 184    NBS 37e    NBS 602    NBS 856    IARM 102A    IARM 111A    IARM 109A    SS 6063 K12    SS 6262AB    SS 852 C20

### Homogeneity and Uncertainty

"Uncertainty" values, as reported adjacent to certified concentration values, are based on a 95% Confidence Interval. These estimated uncertainties include the combined effects of method imprecision, material inhomogeneity, and any bias between methods. Homogeneity data from experimental XRF results are reflected in both the overall statistics and certified data. Homogeneity samples are selected by a systematic sampling procedure. The number of samples may be determined by equation 1, where  $N_{prod}$  is the number of units produced and  $N_{min}$  is the number of samples used for homogeneity testing. These samples are arranged in a simple randomized design such that each sample is analyzed multiple times by XRF. Homogeneity may also be determined within sample using an applied version of ASTM E826. A single factor ANOVA is used to calculate uncertainty due to inhomogeneity ( $U_{hom}$ ). Uncertainty of the material is calculated by equation 2, where  $H=U_{hom}$ ,  $S$ = Standard deviation,  $t$ = t-value at 95% CI, and  $n$ = number of observations.

$$1. N_{min} = \max(10, \sqrt[3]{N_{prod}})$$

$$2. U_{CRM} = \frac{\sqrt{H^2 + S^2}}{\sqrt{n}} * t$$

### Expiration

The certification of this material is valid indefinitely, within the uncertainty specified, provided the material is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the material is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.



David Coler, General Manager

Analytical Reference Materials International

