

CERTIFICATE OF ANALYSIS

55X A30J1 (batch J)

Certified Reference Material Information

Type: ALUMINIUM / SILICON / COPPER (HIPped)
Form and Size: Disc ~65mm diameter
Produced by: RSP Technologies, Delfzijl, Holland
Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

| Element | Cu | Mg | Si | Fe | Mn | Ni | Zn | Pb | Sn |
|--------------------------|-------------|--------------|--------------|--------------|--------------|---------------|--------------|-------------|---------------|
| Value ¹ | 5.08 | 0.866 | 14.92 | 1.125 | 0.101 | 0.0100 | 0.145 | 0.14 | 0.0094 |
| Uncertainty ² | 0.05 | 0.010 | 0.08 | 0.012 | 0.002 | 0.0009 | 0.003 | 0.01 | 0.0004 |

| Element | Ti | Cr | Co | V | Bi | Ca | Be | P |
|--------------------------|--------------|---------------|--------------|---------------|--------------|---------------|---------------|--------------|
| Value ¹ | 0.207 | 0.0075 | 0.074 | 0.0117 | 0.018 | 0.0036 | 0.0048 | 0.006 |
| Uncertainty ² | 0.004 | 0.0006 | 0.003 | 0.0004 | 0.001 | 0.0003 | 0.0002 | 0.001 |

Definitions

- ¹ The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- ² The uncertainty values are generated from the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____

on 11th July 2019

C Eveleigh

Method of Preparation

This reference material was produced using commercial-grade aluminium and master alloys. The melt was rapid-quenched, and the resultant ribbon was milled into powder. The bulk powder was sieved, homogenised, then pressed into a billet which was extruded to bar of the final diameter.

Sampling

Samples for chemical analysis were taken from various positions throughout the batch. Approximately 5% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

Samples representative of the batch were checked for uniformity using an optical emission spectrometer.

From this test data, through-batch variation values were derived for each element as an indicator of any minor compositional variation (as determined for the specific sample size and other limitations of the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025, using documented standard reference methods and validated by appropriate reference materials. The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials.

Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Aluminium alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

Percentage element by weight

| Sample | Cu | Mg | Si | Fe | Mn | Ni | Zn | Pb | Sn |
|--------------------------|--------------|---------------|--------------|--------------|---------------|---------------|---------------|---------------|---------------|
| 1 | 4.980 | 0.8501 | 14.75 | 1.091 | 0.0952 | 0.0076 | 0.1370 | 0.1327 | 0.0083 |
| 2 | 5.027 | 0.8584 | 14.80 | 1.109 | 0.0984 | 0.0077 | 0.1400 | 0.1340 | 0.0087 |
| 3 | 5.035 | 0.8620 | 14.82 | 1.110 | 0.0989 | 0.0090 | 0.1403 | 0.1350 | 0.0091 |
| 4 | 5.037 | 0.8636 | 14.84 | 1.115 | 0.0990 | 0.0093 | 0.1406 | 0.1399 | 0.0091 |
| 5 | 5.039 | 0.8652 | 14.84 | 1.117 | 0.0995 | 0.0095 | 0.1410 | 0.1440 | 0.0092 |
| 6 | 5.062 | 0.8660 | 14.92 | 1.120 | 0.0996 | 0.0096 | 0.1429 | 0.1447 | 0.0092 |
| 7 | 5.088 | 0.8680 | 14.94 | 1.122 | 0.1006 | 0.0097 | 0.1440 | 0.1451 | 0.0094 |
| 8 | 5.096 | 0.8690 | 14.95 | 1.123 | 0.1008 | 0.0099 | 0.1467 | | 0.0094 |
| 9 | 5.117 | 0.8706 | 15.02 | 1.130 | 0.1036 | 0.0103 | 0.1470 | | 0.0095 |
| 10 | 5.122 | 0.8744 | 15.04 | 1.131 | 0.1039 | 0.0105 | 0.1483 | | 0.0096 |
| 11 | 5.153 | 0.8790 | 15.06 | 1.132 | 0.1050 | 0.0105 | 0.1485 | | 0.0098 |
| 12 | 5.160 | | 15.09 | 1.146 | 0.1070 | 0.0109 | 0.1488 | | 0.0098 |
| 13 | | | | 1.149 | | 0.0127 | 0.1498 | | 0.0108 |
| 14 | | | | 1.150 | | 0.0129 | 0.1540 | | |
| Mean | 5.076 | 0.8660 | 14.92 | 1.125 | 0.1010 | 0.0100 | 0.1449 | 0.1393 | 0.0094 |
| Std Dev | 0.055 | 0.0078 | 0.11 | 0.017 | 0.0033 | 0.0015 | 0.0048 | 0.0054 | 0.0006 |
| C_(95%) | 0.037 | 0.0052 | 0.07 | 0.010 | 0.0021 | 0.0009 | 0.0028 | 0.0050 | 0.0004 |

| Sample | Ti | Cr | Co | V | Bi | Ca | Be | P |
|--------------------------|---------------|---------------|---------------|---------------|---------------|---------------|---------------|---------------|
| 1 | 0.1959 | 0.0067 | 0.0691 | 0.0102 | 0.0164 | 0.0032 | 0.0042 | 0.0040 |
| 2 | 0.1991 | 0.0067 | 0.0696 | 0.0112 | 0.0164 | 0.0032 | 0.0044 | 0.0043 |
| 3 | 0.2013 | 0.0069 | 0.0697 | 0.0113 | 0.0166 | 0.0032 | 0.0046 | 0.0047 |
| 4 | 0.2015 | 0.0070 | 0.0699 | 0.0113 | 0.0175 | 0.0034 | 0.0046 | 0.0054 |
| 5 | 0.2057 | 0.0072 | 0.0724 | 0.0114 | 0.0176 | 0.0035 | 0.0047 | 0.0060 |
| 6 | 0.2061 | 0.0072 | 0.0743 | 0.0115 | 0.0182 | 0.0035 | 0.0047 | 0.0065 |
| 7 | 0.2070 | 0.0072 | 0.0743 | 0.0118 | 0.0188 | 0.0037 | 0.0047 | 0.0066 |
| 8 | 0.2070 | 0.0072 | 0.0750 | 0.0120 | 0.0191 | 0.0041 | 0.0047 | 0.0076 |
| 9 | 0.2089 | 0.0076 | 0.0753 | 0.0122 | | 0.0041 | 0.0048 | 0.0077 |
| 10 | 0.2107 | 0.0077 | 0.0762 | 0.0123 | | 0.0041 | 0.0049 | 0.0079 |
| 11 | 0.2138 | 0.0083 | 0.0771 | 0.0124 | | | 0.0049 | |
| 12 | 0.2160 | 0.0084 | 0.0788 | 0.0125 | | | 0.0049 | |
| 13 | 0.2160 | 0.0088 | 0.0788 | | | | 0.0053 | |
| 14 | | | 0.0791 | | | | 0.0053 | |
| Mean | 0.2068 | 0.0075 | 0.0743 | 0.0117 | 0.0176 | 0.0036 | 0.0048 | 0.0061 |
| Std Dev | 0.0063 | 0.0007 | 0.0036 | 0.0007 | 0.0011 | 0.0004 | 0.0003 | 0.0015 |
| C_(95%) | 0.0038 | 0.0004 | 0.0021 | 0.0004 | 0.0009 | 0.0003 | 0.0002 | 0.0011 |

Note: C_(95%) is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

| | | |
|---|--------------------------|---------------------------|
| Element Ltd | Middlesbrough, England | UKAS accreditation 0239 |
| Sheffield Assay Office | Sheffield, England | UKAS accreditation 0012 |
| Anchorcert Analytical | Birmingham, England | UKAS accreditation 0667 |
| Universal Scientific Laboratory Pty Ltd | Milperra, NSW, Australia | NATA accreditation 0492 |
| Shanghai Jinyi Test Technology Co | Shanghai, China | CNAL accreditation 0783 |
| Luo Yang Copper Co | Luo Yang, HeNan, China | CNAS accreditation 0173 |
| Genitest, Inc | Montreal, Canada | PJ accreditation L17-153 |
| Raghavendra Spectromet Laboratory | Bangalore, India | NABL accreditation 0371 |
| Institute of Non-Ferrous Metals | Gliwice, Poland | PCA accreditation AB274 |
| INCDMNR-IMNR | Pantelimon, Romania | RENAR accreditation 1056 |
| Tec-Eurolab | Campogalliano, Italy | ACCREDIA accreditation 52 |
| TCR Engineering Services | Mumbai, India | |
| Mineral & Metallurgical Laboratories | Bangalore, India | |
| AMG Superalloys UK Ltd | Rotherham, England | |
| Scrooby's Laboratory Service | Benoni, South Africa | |
| Analyticka Laborator Lithea sro | Brno, Czech Republic | |

Note: to achieve the above accreditation (UKAS, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

| ELEMENT | RESULT No. & METHOD | | | |
|------------|----------------------|--------------|---------|--------------------------------|
| | ICP-AES | FAAS | | OTHER |
| Copper | 1-5, 8, 9, 11 | 6, 10, 12 | 7 | volumetric (thiosulfate) |
| Magnesium | 1-7, 9-11 | 8 | | |
| Silicon | 1, 4, 5, 9-11 | - | 2, 3 | photometric (molybdenum blue) |
| Iron | 2, 4-6, 8, 9, 11-13 | 1, 3, 10, 14 | 6-8, 12 | gravimetric (perchloric acid) |
| Manganese | 1, 2, 5-10, 12 | 4 | 7 | volumetric (redox) |
| Nickel | 1, 3-7, 9-12, 14 | 8, 13 | 3 | volumetric (bismuthate) |
| Zinc | 1, 3, 4, 6-8, 11-13 | 2, 5, 9, 10 | 11 | photometric (periodate) |
| Lead | 1-7 | | 2 | volumetric (dimethyl glyoxime) |
| Tin | 2-4, 6-8, 10-12 | 5, 9 | 14 | gravimetric (oxide) |
| Titanium | 1-6, 10-13 | 7, 9 | 1 | photometric (phenyl fluorone) |
| Chromium | 1-4, 6-13 | 5 | 13 | volumetric (iodide) |
| Cobalt | 1-4, 6, 7, 9, 11, 13 | 5, 8, 10 | 8 | photometric (peroxide) |
| Vanadium | 2, 3, 5-7, 9-12 | 4 | 12 | photometric |
| Bismuth | 1-3, 5, 6, 8 | 4, 7 | 1, 8 | photometric (5 Br-PADAB) |
| Calcium | 1-4, 6-8 | 5, 9, 10 | | |
| Beryllium | 1, 3-9, 11-13 | 2, 10, 14 | | |
| Phosphorus | 1, 3-8, 10 | - | 2, 9 | photometric (molybdenum blue) |

Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO 17034 and the associated Guides, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

This certification is applicable to the whole of the disc although, in accordance with normal practice for OES use, it may be appropriate to avoid using the central area, of approximately 12mm diameter.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of original analysis. Technical support for this certification will therefore expire in July 2039, although we reserve the right to make changes as issue revisions, in the intervening period.

This sample is also available in the form of chippings.

The analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.