

## CERTIFICATE OF ANALYSIS

**11X HPC3 (batch K)**

### Certified Reference Material Information

Type: HIGH-PHOSPHORUS CAST IRON (CHILL CAST)

Form and Size: Disc ~40mm diameter

Manufactured by: Maybrey Reliance Foundry

Certified and Supplied by: MBH Analytical Ltd

### Assigned Values

#### Percentage element by weight

Element	C	Si	S	P	Mn
Value <sup>1</sup>	3.24	1.378	0.0786	2.52	1.009
Uncertainty <sup>2</sup>	0.03	0.014	0.0013	0.04	0.016

Element	Ni	Cr	Mo	Cu	V
Value <sup>1</sup>	1.52	1.191	0.172	0.132	0.042
Uncertainty <sup>2</sup>	0.02	0.016	0.004	0.004	0.002

### Definitions

- <sup>1</sup> The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- <sup>2</sup> The uncertainties are value judgements, based on 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

### Certified by:

MBH ANALYTICAL LIMITED



on 2<sup>nd</sup> November 2019

C Eveleigh

## **Method of Preparation**

This reference material was produced from commercial-purity metals, and master alloys. The discs are the product of one melt poured into multiple chill moulds with feeding systems designed to ensure sound discs. Approximately 2mm has been removed from the cast faces of the discs to minimise surface effects.

## **Sampling**

Milled samples for chemical analysis were taken from random positions within the casting sequence. In addition, 8% of all discs were selected for homogeneity checking.

## **Homogeneity**

Samples representative of the batch were checked for uniformity using an optical emission spectrometer. Multiple measurements were taken from each surface under test.

Using the meaned data from each surface, standard deviation values were derived for each element as an indicator of any non-homogeneity (as determined for the specific sample size taken by the spectrometer).

## **Chemical Analysis**

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

## **Estimation of Uncertainties**

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ( $C_{(95\%)}$ ) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, discussed above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

## **Traceability**

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials.

Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

## **Usage**

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use: Cast irons are generally prepared by finishing, milling or by machining on a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Important note: For OES, this sample may require up to 120 seconds pre-spark before each analysis.

## Analytical Data

### Percentage element by weight

Sample	C	Si	S	P	Mn
1	3.190	1.356	0.0749	2.445	0.969
2	3.198	1.361	0.0767	2.448	0.978
3	3.215	1.362	0.0774	2.451	0.997
4	3.246	1.365	0.0780	2.485	0.997
5	3.247	1.380	0.0780	2.485	1.009
6	3.250	1.380	0.0781	2.489	1.013
7	3.251	1.381	0.0783	2.520	1.017
8	3.252	1.385	0.0784	2.525	1.018
9	3.254	1.387	0.0788	2.526	1.021
10	3.258	1.390	0.0789	2.532	1.023
11	3.262	1.393	0.0794	2.561	1.029
12	3.269	1.395	0.0794	2.578	1.040
13			0.0801	2.601	
14			0.0806	2.612	
15			0.0817	2.616	
<b>Mean</b>	<b>3.239</b>	<b>1.378</b>	<b>0.0786</b>	<b>2.524</b>	<b>1.009</b>
<b>Std Dev</b>	0.028	0.013	0.0016	0.059	0.021
<b>C (95%)</b>	0.018	0.009	0.0009	0.032	0.013

Sample	Ni	Cr	Mo	Cu	V
1	1.473	1.160	0.1650	0.1218	0.0383
2	1.491	1.169	0.1650	0.1228	0.0389
3	1.502	1.172	0.1663	0.1230	0.0395
4	1.506	1.183	0.1672	0.1262	0.0397
5	1.519	1.184	0.1687	0.1266	0.0397
6	1.520	1.184	0.1690	0.1300	0.0398
7	1.535	1.187	0.1710	0.1324	0.0402
8	1.536	1.193	0.1720	0.1330	0.0404
9	1.537	1.196	0.1730	0.1330	0.0409
10	1.542	1.204	0.1731	0.1355	0.0410
11	1.543	1.211	0.1787	0.1370	0.0423
12	1.549	1.221	0.1798	0.1375	0.0426
13	1.551	1.222	0.1800	0.1377	0.0440
14			0.1820	0.1400	0.0440
15				0.1401	0.0451
<b>Mean</b>	<b>1.523</b>	<b>1.191</b>	<b>0.1722</b>	<b>0.1318</b>	<b>0.0417</b>
<b>Std Dev</b>	0.024	0.019	0.0059	0.0064	0.0038
<b>C (95%)</b>	0.015	0.012	0.0034	0.0035	0.0021

Note:  $C_{(95\%)}$  is the 95% half-width confidence interval derived from the equation:

$$C_{(95\%)} = (t \times SD) / \sqrt{n}$$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

## Participating Laboratories

Element Ltd	Middlesbrough, England	UKAS accreditation 0239
Sheffield Analytical Services	Sheffield, England	UKAS accreditation 0012
Metals Technology (Testing) Ltd	Sheffield, England	UKAS accreditation 0963
Anchorcert Analytical	Birmingham, England	UKAS accreditation 0667
Universal Scientific Laboratory Pty Ltd	Milperra, NSW, Australia	NATA accreditation 0492
Genitest, Inc	Montreal, Canada	PJ accreditation L17-153
Shanghai Jinyi Test Tech Co	Shanghai, China	CNAS accreditation 0041
Luo Yang Copper	Luo Yng, He Nan, China	CNAL accreditation 0173
Raghavendra SpectroMet Laboratory	Bangalore, India	NABL accreditation 0371
TCR Engineering Services Ltd	Mumbai, India	NABL accreditation 0367
Instytut Metalurgii Zelaza	Gliwice, Poland	PCA accreditation AB554
Tec-Eurolab	Campogalliano, Italy	ACCREDIA accreditation 52
TUV Nord Czech	Brno, Czech Republic	CAI accreditation L1060
INCDMNR-IMNR	Pantelimon, Romania	
Mineral & Metallurgical Laboratories	Bangalore, India	
AMG Superalloys UK Ltd	Rotherham, England	
LGC Standards	Manchester, NH, USA	
Analyticka Laborator Lithea sro	Brno, Czech Republic	

Note: to achieve the above accreditation (UKAS, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

## Analytical Methods Used

ELEMENT	RESULT No. & METHOD		
	ICP-AES	FAAS	OTHER
Carbon	-	-	all combustion (infra-red detection)
Silicon	1, 4, 5, 9, 11, 12	-	3, 6, 10 gravimetric (perchloric acid)
Sulfur	2, 7	-	2, 7, 8 photometric (molybdenum blue)
Phosphorus	3-8, 11, 13-15	-	1, 3-6, 8-15 combustion (IR or volumetric detection)
Manganese	3, 4, 6-10	5, 11, 12	1, 2 volumetric (alkalimetric)
Nickel	1, 3-5, 7-10, 12	6, 11, 13	9, 10, 12 photometric (molybdenum blue)
Chromium	3, 6-13	2	1, 2 volumetric (arsenite, FAS)
Molybdenum	1-5, 8-13	6, 7, 14	2 gravimetric (dimethyl glyoxime)
Copper	1, 2, 4-12, 15	3, 13, 14	1, 4, 5 volumetric (ferrous ammonium sulfate)
Vanadium	1, 3, 5-11, 13, 15	2, 4, 12	14 volumetric (ferrous ammonium sulfate)

## Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO 17034 and the associated guides, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of chill casting, have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc, to a depth of 12mm. Material to the rear of the disc, to a depth of ~3 mm, is not certified.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in November 2039, although we reserve the right to make changes as issue revisions, in the intervening period.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.