32X LB15 F Page 1 of 4 March 2020



CERTIFICATE OF ANALYSIS

32X LB15 (batch F)

Certified Reference Material Information

Type: LEADED BRONZE (CHILL CAST)

Form and Size: Disc ~40mm diameter

Manufactured by: Maybrey Reliance Foundry

Certified and Supplied by: MBH Analytical Ltd

Assigned Values

Percentage element by weight

Element	Sn	Pb	Zn	Fe	Ni	Р	As	Bi
Value ¹	4.53	20.15	0.147	0.0039	0.104	0.063	0.0163	0.129
Uncertainty ²	0.04	0.09	0.002	0.0006	0.001	0.002	0.0008	0.003

Element	Sb	Ag	S	Al	Si	Со	Cd	Cu
Value ¹	0.198	0.023	0.021	0.0009	0.0018	0.0004	0.0006	74.5
Uncertainty ²	0.004	0.001	0.002	0.0006	0.0004	0.0001	0.0002	0.2

Note: values given in parentheses are not certified - they are provided for information only.

Definitions

- The certified values are the present best estimates of the true content for each element. Each value is a panel consensus, based on the averaged results of an interlaboratory testing programme, detailed on page 3.
- The uncertainties are value judgements, based on the 95% confidence interval derived from the wet analysis results, in combination with a statistical assessment of the homogeneity data, as described on page 2.

Certified by:

MBH ANALYTICAL LIMITED _____ on 27th March 2020

C Eveleigh

Method of Preparation

This reference material was produced from commercial-purity metals, and master alloys. The discs are the product of one melt poured into a sequence of multiple chill moulds with feeding systems designed to ensure sound discs. Approximately 2mm has been removed from the cast faces of the discs to minimise surface effects.

Sampling

Samples for chemical analysis were taken from various positions throughout the casting process. At least 15% of all discs were selected for non-destructive homogeneity testing.

Homogeneity

Samples representative of the batch were checked for uniformity using an optical emission spectrometer.

For all accepted material, through-batch variation values were derived for each element as an indicator of any minor compositional variation (as determined for the specific sample size and other limitations of the spectrometer).

Chemical Analysis

Analysis was carried out on millings taken from samples representative of the product. It was performed by a panel of laboratories mostly operating within the terms of EN ISO/IEC 17025, using documented standard reference methods and validated by appropriate reference materials.

The individual values listed overpage are the average of each analyst's results.

Estimation of Uncertainties

Each element certified has been analysed by several laboratories, and 95% half-width confidence intervals ($C_{(95\%)}$) for the resultant mean values have been derived by the method shown on page 3.

As a separate exercise, the degree of non-homogeneity of the batch for each element has been quantified by a programme of non-destructive application testing, described above.

The final certified uncertainty for each element has been derived by combining these two factors, using the square-root of the summed squares.

Traceability

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognised reference materials.

Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

Usage

Intended use: With optical emission and X-ray fluorescence spectrometers.

Recommended method of use:

Copper alloys are generally prepared by machining on a mill or a lathe. However, users are recommended to follow the calibration and sample preparation procedures specified by the relevant instrument manufacturer.

Preparation should be the same for reference materials and the samples for test.

A minimum of five consistent replicate analyses is recommended to provide the necessary sample size. Users are advised to check against possible bias between reference materials and production samples due to differences in metallurgical history, and be aware of possible inter-element effects.

Analytical Data

			<u>Percentaç</u>	ge element b	y weight			
Sample	Sn	Pb	Zn	Fe	Ni	Р	As	Bi
1	4.429	19.96	0.1397	0.0021	0.1007	0.0590	0.0143	0.1220
2	4.470	20.00	0.1410	0.0031	0.1010	0.0618	0.0153	0.1230
3	4.474	20.02	0.1440	0.0031	0.1010	0.0623	0.0158	0.1272
4	4.484	20.04	0.1459	0.0034	0.1030	0.0633	0.0161	0.1285
5	4.509	20.05	0.1467	0.0035	0.1040	0.0636	0.0163	0.1293
6	4.524	20.12	0.1470	0.0036	0.1040	0.0637	0.0169	0.1308
7	4.545	20.16	0.1472	0.0037	0.1042	0.0640	0.0170	0.1318
8	4.579	20.22	0.1487	0.0045	0.1050	0.0667	0.0173	0.1320
9	4.588	20.27	0.1489	0.0045	0.1060		0.0177	0.1364
10	4.593	20.29	0.1492	0.0048	0.1060			
11	4.602	20.33	0.1503	0.0048	0.1070			
12		20.38	0.1505	0.0050				
13			0.1510	0.0052				
14			0.1518					
Mean	4.527	20.15	0.147	0.0039	0.1038	0.0631	0.0163	0.1290
Std Dev	0.059	0.14	0.0036	0.0009	0.0022	0.0022	0.0011	0.0045
C _(95%)	0.04	0.09	0.002	0.0006	0.001	0.002	0.0008	0.003
Sample	Sb	Ag	S	Al	Si	Со	Cd	Cu
1	0.1895	0.0203	0.0184	0.0001	0.0011	0.0002	0.0003	74.25
2	0.1930	0.0212	0.0194	0.0001	0.0012	0.0002	0.0003	74.27
3	0.1931	0.0213	0.0196	0.0003	0.0015	0.0003	0.0003	74.27
4	0.1953	0.0214	0.0202	0.0006	0.0017	0.0003	0.0004	74.43
5	0.1957	0.0234	0.0208	0.0014	0.0018	0.0005	0.0005	74.51
6	0.1967	0.0236	0.0224	0.0015	0.0019	0.0005	0.0005	74.58
7	0.1968	0.0237	0.0227	0.0015	0.0019	0.0006	0.0008	74.63
8	0.2027	0.0238	0.0249	0.0016	0.0021	<0.0005	0.0008	74.76
9	0.2030	0.0242	0.0250		0.0026	<0.0005	0.0009	74.77
10	0.2030	0.0249			0.0026	<0.001	0.0010	
11	0.2070	0.0260					0.0010	
12		0.0281						
Mean	0.1978	0.0235	0.0215	0.0009	0.0018	0.0004	0.0006	74.5
Std Dev	0.0054	0.0022	0.0024	0.0007	0.0005	0.0002	0.0003	0.21
C _(95%)	0.004	0.001	0.002	0.0006	0.0004	0.0001	0.0002	0.2

Note: $C_{(95\%)}$ is the 95% half-width confidence interval derived from the equation:

 $C_{(95\%)} = (t \times SD)/\sqrt{n}$

where n is the number of available values, t is the Student's t value for n-1 degrees of freedom, and SD is the standard deviation of the test results.

Participating Laboratories

Element Ltd
Sheffield Assay Office
Anchorcert Analytical
Universal Scientific Laboratory Pty Ltd
Genitest, Inc
Shanghai Jinyi Test Technology Co
Luo Yang Copper
Raghavendra Spectromet Laboratory
TCR Engineering Services Pvt Ltd
Institute of Non-Ferrous Metals
TEC-Eurolab SRL
INCDMNR-IMNR
Mineral & Metallurgical Laboratories
AMG Superalloys UK Ltd
Analyticka Laborator Lithea sro

Middlesbrough, England Sheffield, England Birmingham, England Milperra, NSW, Australia Montreal, QC, Canada Shanghai, China Luo Yang, He Nan, China Bangalore, India Mumbai, India Gliwice, Poland Modena, Italy Pantelimon, Romania Bangalore, India Rotherham, England Brno, Czech Republic UKAS accreditation 0239 UKAS accreditation 0012 UKAS accreditation 0667 NATA accreditation 0492 PJ accreditation L17-153 CNAL accreditation 0783 CNAL accreditation 0173 NABL accreditation 0371 NABL Accreditation 0367 PCA accreditation AB274 Accredia accreditation 52

Note: to achieve the above accreditation (UKAS, etc), test houses must demonstrate conformity to the general requirements of EN ISO/IEC 17025.

Analytical Methods Used

ELEMENT		RESULT No. & METHOD					
	ICP-AES	FAAS		OTHER			
Tin	1, 3, 4, 6, 9-11	-	2, 7, 8	volumetric (iodate)			
			5	photometric (phenyl fluorone)			
Lead	2, 3, 10, 12	4, 6, 8	1, 7, 9	photometric			
			5, 11	gravimetric (sulfate)			
Zinc	1, 3, 5-7, 9-12, 14	4, 8, 13	2	volumetric (EDTA)			
Iron	1-4, 6, 9-11, 13	5, 7, 12	8	photometric (orthophenanthroline)			
Nickel	1-7, 10	8, 11	9	gravimetric (dimethyl glyoxime)			
Phosphorus	2, 7, 8	-	1, 4	volumetric (alkalimetric)			
			3, 5, 6	photometric (molybdenum yellow)			
Arsenic	1-7, 9	8					
Bismuth	1-7	8, 9					
Antimony	1, 2, 4, 6-10	3, 5	11	photometric (crystal violet)			
Silver	1, 3, 5, 6, 9-11	2, 7, 8, 12	4	gravimetric (chloride)			
Sulfur	4, 6	-	1-3, 5, 7-9	combustion (IR or volumetric detection)			
Aluminium	2-6, 8	1, 7					
Silicon	1, 2, 5-10	-	3, 4	photometric (molybdenum yellow)			
Cobalt	2, 4-10	1, 3					
Cadmium	2, 3, 5, 8-11	1, 4, 6, 7					
Copper	4, 8	-	1, 5, 9	volumetric (thiosulfate)			
			2, 3, 6, 7	electrogravimetric			

Notes

This Certified Reference Material has been produced and certified, wherever possible, in accordance with the requirements of ISO 17034 and the associated Guides, taking into account the requirements of the ISO Guide to the Expression of Uncertainty in Measurement (GUM).

The unidirectional solidification effects associated with this method of chill casting, have led to the formation of inhomogeneous segregates in the rear portion of the disc. The above certification is therefore only applicable from the front face of the disc, to a depth of 10mm. Material to the rear of the disc, to a depth of ~5 mm, is not certified.

This material will remain stable indefinitely, provided adequate precautions are taken to protect it from cross-contamination, extremes of temperature and atmospheric moisture. All production records will be retained for a period of 20 years from the date of this certificate. Technical support for this certification will therefore expire in November 2039, although we reserve the right to make changes as issue revisions, in the intervening period.

This material is also available in the form of chippings, for the calibration or control of methods involving dissolution.

The manufacture, analysis and certification of this product were supervised by C Eveleigh, PhD, Technical Director, MBH Analytical Ltd.

The material to which this certificate of analysis refers is supplied subject to our general conditions of sale.