

UV Cure Wood Sealer

VITRECURE 6

PRODUCT DESCRIPTION: A & I Coatings VITRECURE 6 is a high cure speed UV Cure Sealer for very porous timbers such as balsa. It is sandable and readily receives most top coats. VC6 provides an excellent bond surface for polyester or epoxy resins as has been proven by our research and major industry validation.

TYPICAL APPLICATIONS:

- Balsa wood for inclusion in composite applications.

TECHNICAL INFORMATION

Vehicle Type : UV Curable Acrylic.
Finish : Gloss.
Colour : Clear .
Dry time : Cures in less than a second under UV lights.

Recoat time (minimum) : Sanding is necessary before recoating.

Theoretical Coverage : 50m²/L@20µm.
Volume Solids : 100%.
Recommended DFT : 10gsm to 25gsm.
Usual no. of coats : 1 coat.
Flexibility : Adequate for all normal applications.
Abrasion Resistance : Good.
Bacterial Resistance : Good.
Chemical Resistance : Excellent.
Heat Resistance : 120°C.
Solvent Resistance : Excellent.
Thinning and cleaning : No thinning required. Clean with Acetone or Ethyl acetate.
Durability : Good.
Product weight : 1.14Kg/ Litre.
VOC Content : <5 grams/ Litre.
Cure Speed : Up to 10m/ Min.
Lamps : 1 x 80w/cm MPHg (medium Pressure Mercury Vapour) Lamps

MERITS:

1. Low monomer content
2. Low porous substrate absorption
3. Fast cure
4. Low odour
5. Excellent sealing properties for balsa wood

LIMITATIONS:

1. In cold temperatures, VC6 may need to be heated or warmed up to achieve right application viscosity.

APPLICATION DATA

Equipment : Roller coater

Cleaning : Acetone

Typical Specification : Wood coating
Roller apply 15µm on timber
Cure 10m/min. 1 x MPHg Lamp C80W/cm).

SURFACE PREPARATION:

Ensure surface is free of grease or other contaminations. Porous surface may help for the coating to achieve better adhesion.

WORK STOPPAGES : Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with **A & I Coatings** recommended cleaner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.

CLEAN UP : Clean all equipment after use with **A & I Coatings** recommended cleaner. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including and delays.

PACKING & STORAGE

Packing : Available in 21kg pails. For availability of other sizes, contact **A & I Coatings**.

Storage : 12 months if stored in sealed containers away from heat and moisture. Subject to re-inspection thereafter.

HEALTH AND SAFETY : All applicable statutory regulations must be observed in the application of this product. Users must first read the Material Safety Data Sheet for Vitrecure 6. Users should familiarise themselves with all the safety aspects of the product prior to usage.

Please ensure the current Technical Data Sheet is consulted prior to specification or application of **A & I Coatings** products. If the surface intended to be painted differs from the specification, please consult the **A & I Coatings** Technical team on 1800 819 585.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on site conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation.

DISCLAIMER

Since the use and application of this product is beyond our control we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty.

For additional information, phone our Customer Service Centre on **1800 819 585**.

APRIL 2010 - THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED.