

ENVIROTHANE 8476



Water Based Two Pack Urethane Topcoat

Technical Data Sheet Number 280



PRODUCT DESCRIPTION	A & I Coatings ENVIROTHANE 8476 is a water borne two pack polyurethane coating which gives excellent adhesion, barrier and film properties on a variety of substrates. It is easy to use and environmentally friendly, with the added benefit of durability, good yellowing and UV resistance on exterior exposure. It has good abrasion and chemical resistance.				
USES & BENEFITS	<ul style="list-style-type: none"> • Cabinetry and joinery • Architectural and decorative steelwork • Concrete and masonry topcoat 				
	<u>Benefits</u> <ol style="list-style-type: none"> 1. Excellent weathering performance 2. High gloss up to 92% 60° can easily be achieved 3. Good chemical resistance 4. Good mechanical properties 	<u>Limitations</u> <ol style="list-style-type: none"> 1. Not to be applied at very low temperatures or high humidity (<10°C and over 75% R.H.) 2. Prone to bubbling if applied too thick (over 400 micron WFT) 3. Excessive thickness could cause whitening 			
PHYSICAL PROPERTIES	Vehicle Type	Polyurethane			
	Hardener	Water dispersible isocyanate			
	Mixing Ratio	6:1 (Pack A : Pack B) by Volume			
	Pot Life	2 – 3 hours@25°C			
	Finish	Gloss, Semi Gloss 50%, Satin 30% or Matt 10%			
	Theoretical Coverage	8.2m ² /L@ 50µm DFT(120µmWFT) for clear, 10.0m ² /L@ 50µm DFT(100µmWFT) for white			
	Volume Solids	42% for clear, 50% for white			
	Recommended DFT	Typically 50 – 75 microns dependent on substrate			
	Usual No. of Coats	1 - 2			
	Primer Required	Yes, dependant on substrate. Contact A & I Coatings for specific applications			
	Colour	Clear or pigmented			
	Pigmentation	Various			
	Product Weight	1.02 – 1.31Kg/Litre			
	VOC Content	41grams/Litre			
ENGINEERING DATA	Abrasion Resistance	Excellent			
	Flexibility	Very good			
	Bacterial Resistance	Excellent			
	Chemical Resistance	Very good to a wide range of chemicals. Contact A & I Coatings for specific requirements			
	Dry Heat Resistance	120°C			
	Solvent Resistance	Good			
	Salt Spray Resistance	Good			
	Durability	Excellent			
CURING DATA	Substrate Temp.(°C)	Touch Dry	Dry to Handle	Full Cure	Recoat Min
	10 °C				
	25 °C	45 Min	3 Hrs	7 Days	2 – 8Hrs
	40 °C				
	Note	May be recoated after tack dry e.g. 2-8 hours @ 25°C. N.B. Best results are achieved with (minimum) a light coat first followed by a double header coat when the water has flashed off			

APPLICATION DATA	Mixing	Power stir Pack A with Pack B thoroughly for at least 2 minutes, without causing an excess of foam, before thinning. Thin 5-10% with water as necessary and gently stir.
	Application	Air or Airless Spray, brush, or roller. (A & I Coatings technical staff can advise on the most appropriate equipment for a specific task).
	Thinning	Water
	Cleaning	Water
	Typical Specification	<u>Concrete coating:</u> One coat E2100 undercoat applied as per E2100 TDS (or E2000 for clear). One coat E8476 topcoat at 50 micron DFT. Fully cured in 7 days. For other substrates contact A & I Coatings, or visit our website on www.aicoatings.com .
WORK STOPPAGES	General	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with A & I Coatings recommended cleaner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.
	Clean Up	Clean all equipment after use with A & I Coatings recommended cleaner. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, (including delays).
PACKING & STORAGE	Packing	Available in 7L or 14L kits. For availability of other sizes, contact A & I Coatings.
	Storage	12 months if stored in sealed containers away from heat and moisture. Subject to re-inspection thereafter.
HEALTH & SAFETY	<p>All applicable statutory regulations must be observed in the application of this product. Users must first read the Material Safety Data Sheet for Envirothane 8476. Users should familiarise themselves with all the safety aspects of the product prior to usage.</p> <p>Please ensure the current Technical Data Sheet is consulted prior to specification or application of A & I Coatings products. If the surface intended to be painted differs from the specification, please consult the A & I Coatings Technical team on 1800 819 585.</p>	

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on onsite conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation. **DISCLAIMER** Since the use and application of this product is beyond our control, we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty. For additional information, phone our Customer Service Centre on 1800 819 585, or e-mail helpdesk@aicoatings.com Visit our website for more products: www.aicoatings.com

May 2019 - THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED.