



**DIVERSIFIED**  
**TESTING LABORATORIES, Inc.**  
 WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
 P.O. BOX 4004  
 BURLINGTON, NORTH CAROLINA 27215  
 PHONE (336) 227-7710 • FAX (336) 227-1175  
 www.diversifiedtestinglabs.com

June 15, 2015

Mr. Lee Hinsley  
 GLOBAL PLASTIC SHEETING  
 1331 Specialty Drive  
 Vista, CA 92081

Reference: Laboratory Test Report  
 Lab Identification No. 15474  
 Invoice No. 46287 (Attached)

Dear Mr. Hinsley:

One (1) sample, identified as **ULTRA DECKPROTEK FR 30**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	2.06
2	0.0	0.66
3	0.0	8.03
4	0.0	3.91
5	0.0	3.34
6	0.0	3.20
7	0.0	4.61
8	0.0	2.48
9	0.0	2.47
10	0.0	3.13
AVG.	0.0	3.39

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr  
 Attachment