

Property	Test Standard	Specification						
Compressive	ASTM C-579-01 (12)	12,280 psi at 7 days						
Tensile	ASTM C-307	7,100 psi						
Flexural	ASTM C-580-02	14,800 psi						
Tensile Adhesion Strength	ASTM D7234	1635 psi with quarry tile failure						
Flammability	ASTM D-635	Self-extinguishing						
Taber Abrasion-Resistant	ASTM C-501-84 (09)	H-22 Wheels - 2263 Wear Index						
Impact Resistant	ASTM D-2794-93 (10)	60 in-lbs						
Water Absorption	ASTM D-570	0.28% increase						
Slip Resistance	ASTM F-1679	<table border="0"> <tr> <td><u>Dry</u></td> <td><u>Wet</u></td> <td><u>Oily</u></td> </tr> <tr> <td>0.86</td> <td>0.80</td> <td>0.25</td> </tr> </table>	<u>Dry</u>	<u>Wet</u>	<u>Oily</u>	0.86	0.80	0.25
<u>Dry</u>	<u>Wet</u>	<u>Oily</u>						
0.86	0.80	0.25						
Temp. Resistance	ASTM D-2794	150-200F No visible softening, cracking or delaminating						
Coefficient of Linear Expansion	ASTM D-696	$4.29 \times 10^{-5} 1^{\circ}\text{C}$						
Smoke Density	ASTM D-2843	<3 pass						
Flash Point	D-1929	TBD						
Indentation	ASTM D-2794	Shall not exceed 1% Results 0.8%						
Flame Spread	ASTM E-84	<3 Class A						
VOC content	ASTM D-3960	0.1019 lb/gal						