IMSL

CERTIFICATE OF ANALYSIS P						Page 1 of 1
CUSTOMER BioCote Ltd Wolverhampton Science Park Technology Centre Glaisher Drive Wolverhampton WV10 9RU.	ζ.		•=	TICATE NO. MER REF.	101:	3998.28/4628 10/228
SAMPLE DETAILS CONTOUR CASINGS			DATE F ORDER	RECEIVED		07/06/2010
METHOD: Determination of Antibacterial Activity using Test Based on MOD JIS Z 2801:2000						
DATE ANALYSED RESULTS (AS CFU CM ⁻²)	09/06/2010	DATE REPORTED			11/06/2010	
SAMPLE		SPECIES	CONTACT TIME		REDUCTION (CONTROL)	
			0 hrs	24 hrs	Log 10	%
POLYSTYRENE METAL PANELS POLYSTYRENE METAL PANELS		E coli E coli MRSA MRSA	1.9E+04 1.9E+04 2.2E+04 2.2E+04	3.0E+05 2.3E+01 4.2E+03 < 11.11	4.1 ≥ 2.57	≥ 99.99% ≥ 99.73%

Key: NS = Poor survival on control supplied.

The above data shows the difference in the population following contact with the surface of the samples listed for 24 hours at 35° C under a RH of > 95% relative to the control sample.

IMSL MICROBIOLOGICAL SERVICES LTD PALE LANE HARTLEY WINTNEY HANTS RG27 8DH UK

MANAGING DIRECTOR Peter D Askew

Industrial Microbiological Services Ltd Registered in England No 3264423 Registered Office The Oddfellows Hall Oxford Road Reading Berkshire RG1 7NG