

**CERTIFICATE OF ANALYSIS**

**CERTIFICATE NO.** 1006293.49/1238

**CUSTOMER**

**CUSTOMER REF.** 07/008

BioCote Ltd  
 Wolverhampton Science Park  
 Technology Centre  
 Glaisher Drive  
 Wolverhampton  
 WV10 9RU

**SAMPLE DETAILS**

**DATE RECEIVED** 04/01/2007

CONTOUR CASINGS

**ORDER NO.**

METHOD: Determination of Antibacterial Activity using Test Based on JIS Z 2801: 2000

**DATE ANALYSED** 10/01/2007

**DATE REPORTED** 12/01/2007

**RESULTS (AS CFU CM<sup>-2</sup>)**

SAMPLE	SPECIES	CONTACT TIME		REDUCTION (INITIAL)	
		0 hrs	24 hrs	Log 10	%
TEST PLATE (29:B4000:102 WHITE)	E coli	1.7E+04	< 11.11	≥ 3.18	≥ 99.93%
TEST PLATE (29:B4000:102 WHITE)	MRSA	2.2E+04	< 11.11	≥ 3.30	≥ 99.95%

The above data shows the change in population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95%

INDUSTRIAL MICROBIOLOGICAL SERVICES LTD  
 PALE LANE  
 HARTLEY WINTNEY  
 HANTS  
 RG27 8DH  
 UK

Peter D Askew  
 Managing Director

