

PRODUCT DESCRIPTION

A modified silicone heat resistant coating designed for rapid curing and good working properties over ferrous and non-ferrous metal surfaces. This product is also sold as 62H290.

Color: Black
Sheen: Satin

Benefits

Heat Resistant
Exterior Durable

PRODUCT AND PERFORMANCE DATA

Product Data

| Property | Result |
|--|--|
| Volume solids (%) | 13.04 |
| Weight solids (%) | 22.98 |
| VOC | 749.62 g/l 6.26 lb/gal |
| Recommended dry film thickness | 0.8 to 1.2 mils 20.3 to 30.5 µm |
| Theoretical Coverage @ 1.0 mil (25.4 µm) | 213.9 ft ² / gal 5.3 m ² /L |
| Viscosity (#4 Ford) | 36 – 40 seconds |
| Dry to handle | 30 minutes |

Performance Data

| Test Method | Standard | Result |
|------------------------|-----------------|--|
| Gloss @ 60° | ASTM D523-14 | 2 – 5 |
| Pencil Hardness | ASTM D3363 | H |
| Salt Fog | ASTM B117/D1654 | 240 hours |
| Accelerated Weathering | ASTM D4587-11 | 100 % gloss retention 300 hours QUV A |

Coating Post Burn Performance Results

| Test | Temperature Tested | Time | Result | Method |
|---------------------|--------------------|---------|--------|----------------|
| Color after burn | 1100°F (593°C) | 8 hours | Pass | Muffle Furnace |
| Adhesion after burn | 1200°F (648°C) | 1 hour | 4B | Muffle Furnace |

SURFACE PREPARATION

Pre-cleaning:

Clean all surfaces to be coated in accordance with SSPC-SP-1, Solvent Cleaning prior to additional surface preparation or coating application. Surface must be clean, dry and free of any dirt, dust, oil, and all other visible contaminants.

Surface Preparation

| | |
|-------------|---|
| Recommended | SSPC SP 6 (commercial blast cleaning) |
| Minimum | SSPC SP 2 or SP 3 (hand or power tool cleaning) |

MIXING AND THINNING

Mix Directions

Stir thoroughly before and occasionally during use.

Thinning Directions

Product packaged ready to apply. If needed thin up to 10% maximum with Toluene.

APPLICATION

Application Parameters

| | |
|---------------------|-------------|
| Relative Humidity | 50 % ±10 |
| Minimum Temperature | 50°F (10°C) |
| Maximum Temperature | 80°F (27°C) |

* We recommend allowing product to air dry for 4 hours before putting into service.

Force Cure Schedule

| | |
|-------------|--------------|
| Temperature | 200°F (93°C) |
| Time | 20 minutes |

Application methods

The product can be applied by

Spray

Airless or air assist spray: 0.011 – 0.015 orifice size (in)

Conventional spray: 1.0 – 1.8 orifice size (mm)

*Aerosol touch-up available upon request. Contact your Technical Sales Representative for additional information.

PACKAGING AND STORAGE

Packaging

1 – Gallon
5 – Gallon
Drums

Storage

The product must be stored in accordance with local and national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C) = 12 months *

*When kept in recommended storage condition and original unopened containers.

CAUTION

Adequate health and safety precautions should be observed during storage, handling, use and curing periods.

READ SAFETY DATA SHEETS BEFORE USING THIS PRODUCT

DISCLAIMER

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental or consequential damages.