

PRODUCT DESCRIPTION

A modified Silicone heat resistant coating designed for rapid curing and good working properties over ferrous and non-ferrous metal surfaces.

Color: Black
Sheen: Flat

Benefits

Superior hardness
 Excellent adhesion across multiple substrates
 Low VOC

PRODUCT AND PERFORMANCE DATA
Product Data

Property	Result
Volume solids (%)	13.7 ± 2
Weight solids (%)	25.4 ± 2
VOC	416.56 g/L (3.48 lb/gal)
Theoretical Coverage at 1.0 mil (25.4 µm)	219.7 ft ² /gal (5.4 m ² /L)
Recommended dry film thickness	0.8 – 1.2 mils 20.3 - 30.5 µm
Recommended wet film thickness	5.8 – 8.8 mils 147 – 224 µm
Dry to handle	30 minutes

Performance Data

Test Method	Standard	Result
Gloss @ 60°	ASTM D523-14	2 - 3
Adhesion	ASTM D3359	5B
Pencil Hardness	ASTM D3363	2H
Impact Resistance	ASTM D2794-90	120 in-lbs

Coating Post Burn Performance Results

Test	Temperature Tested	Time	Result	Method
Color after burn	800°F (427°C)	8 Hours	Pass	Muffle Furnace
Adhesion after burn	1000°F (538°C)	1 Hours	5B	Muffle Furnace

**gloss loss observed at the temperatures above*

SURFACE PREPARATION
Pre-cleaning:

Clean all surfaces to be coated in accordance with SSPC-SP-1, Solvent Cleaning prior to additional surface preparation or coating application. Surface must be clean, dry and free of any dirt, dust, oil, and all other visible contaminants.

Surface Preparation

Recommended	SSPC SP 6 (commercial blast cleaning)
Minimum	SSPC SP 2 or SP 3 (hand or power tool cleaning)

MIXING AND THINNING
Mix Directions

Stir thoroughly before and occasionally during use.

Thinning Directions

Product packaged ready to apply. If needed thin up to 10% maximum with Acetone.

APPLICATION
Application Parameters

Relative Humidity	50 % ±10
Minimum Temperature	50°F (10°C)
Maximum Temperature	80°F (27°C)

* We recommend allowing product to air dry for 4 hours before putting into service.

Force Cure Schedule

Temperature	200°F (93°C)
Time	20 minutes

Application methods

The product can be applied by

Spray

Airless spray: 0.009" - 0.015" orifice size

Conventional spray: 0.8 mm – 1.4 mm

*Aerosol touch-up available upon request. Contact your Technical Sales Representative for additional information.

PACKAGING AND STORAGE**Packaging**

1 – Gallon

5 – Gallon

Drums

Storage

The product must be stored in accordance with local and national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C) = 12 months *

*When kept in recommended storage condition and original unopened containers.

CAUTION

Adequate health and safety precautions should be observed during storage, handling, use and curing periods.

READ SAFETY DATA SHEETS BEFORE USING THIS PRODUCT

DISCLAIMER

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental or consequential damages.