



## 60 mil FiberTite-XTreme FB

### Product Data

Seaman Corporation's 60 mil FiberTite-XTreme FB "fleece back" features a 46 x 44 / 1,000 x 1,000 denier woven polyester fabric, coated with a proprietary compound, utilizing DuPont's™ Elvaloy® Ketone Ethylene Ester (KEE) as the principle polymer in the hybrid vinyl alloy coating.

#### DESCRIPTION

60 mil FiberTite-XTreme FB "fleece back" is an 57-oz sq. yd/ minimum 60-mil (1.5 mm) thick membrane. 60 mil FiberTite-XTreme FB is the most intense thermoplastic membrane available. 60 mil FiberTite-XTreme FB has no equal and surpasses the minimum physical property requirements enumerated in ASTM D6754-15 Standard Specification for Ketone Ethylene Ester (KEE) Based Sheet Roofing.

The 60 mil FiberTite-XTreme FB membrane incorporates a 4-oz per sq. yd non-woven polyester felt, heat bonded to the back side of the membrane with a 3-in selvage edge for field welding. 60-mil FiberTite-XTreme FB is manufactured in conventional 72-in by 80-ft roll goods.

Seaman Corporation is vertically integrated, which allows complete control over the manufacturing process from the selection of the yarns, to the engineering, knitting and weaving of the base fabrics to the final coating process. Today, FiberTite Roofing Membranes are the result of Seaman Corporation's 60 years of applied fabric engineering and coating technology.

All FiberTite Roofing Membranes are constructed using high tenacity/heavy weight yarns to create a base fabric reinforcement to impart superior puncture, tensile and tear resistance properties. The base polyester fabrics are primed with a unique and proprietary adhesive coat that lays the foundation to physically bond the KEE coatings to the "fiber" to maximize seam strength and overall membrane performance.

60 mil FiberTite-XTreme FB is coated on the face with Seaman Corporation's original "KEE" formulation to provide superior hot air welding characteristics, extreme UV resistance, broad chemical resistance and long-term flexibility and reparability for the installed roofing membrane system. The back side of the membrane is coated with a slightly modified version of Seaman Corporation's original KEE compound. Additionally, 60 mil FiberTite-XTreme FB exhibits extreme puncture and tear resistance for the most abusive roof areas as well as the historical fungus, algae and flame resistance that make FiberTite Roofing Systems some of the most sustainable roofing systems available.

60 mil FiberTite-XTreme FB membrane is manufactured in conventional 72-in by 80-ft roll goods. Field seaming of the membrane is accomplished by fusing the thermoplastic membrane with conventional hot air welding equipment.

#### PHYSICAL PROPERTIES

ASTM D6754-15	Minimum Requirements	60 mil XTreme FB Typical
Thickness, mm (in.) ASTM D 751	0.81 (0.032)	1.53 (0.060 min.)
Thickness over Fiber, mm (in) Optical method (inches)	0.18 (0.007)	.53 (0.021)
Breaking Strength, N (lbf) ASTM D 751 proc. B - strip	1499 (338)	3078 (692)
Elongation at Break, % ASTM D 751 - strip	18	30
Tear Strength, N (lbf) ASTM D 751 Proc. B. Tongue Tear	338 (76)	667 (150)
Linear Dimensional Change ASTM D 1204 max (%)	1.3	0.5
Fabric Adhesion, N/m (lbf/in) ASTM D 751	3330 (19)	260 (15)
Retention of Properties after Heat Aging ASTM D 3045 - 176°/56 days Breaking Strength, strip, % original Elongation at Break, strip, % original	90 90	90 90
Low Temperature Bend after Heat Aging	-30	-40
Low Temperature Bend ASTM D 2136 (°f)	-30	-40
Change in Weight after Exposure in Water D 471 158°f, 166 h, one side only, max. (%)	0.0, +6.0	0.0, +3.7
Factory Seam Strength, N (lbf) ASTM D 751 Grab Method	1955 (440)	90% of Fabric Break
Hydrostatic Resistance, Mpa (psi) ASTM D751	4.1 (590)	6.9 (1000)
Static Puncture Resistance ASTM D 5602 (99 lbf)	pass	pass
Dynamic Puncture Resistance (J) ASTM D 5635	10	> 50



For more information on FiberTite Systems and accessories please call:  
Seaman Corporation (800) 927-8578  
International (330) 262-1111  
www.fibertite.com

**INTELLIGENT**  
ROOFING SOLUTIONS

FiberTite® is a registered trademark of Seaman Corporation.



As to an external fire exposure only. See UL directory of products certified for Canada and UL roofing materials and systems directory 34KL, 48P0, 97P9.



CHEMICAL FABRICS & FILM ASSOCIATION, INC.

DC196

CHARTER MEMBER



These specifications are current as of the date of printing. Revisions or additions may be issued periodically. For a listing, presentation, and download of the most recent data, visit:

[www.fibertite.com/document-library/product-data-sheets](http://www.fibertite.com/document-library/product-data-sheets)

# 60 mil FiberTite-XTreme FB

## Product Data

### APPLICATION

60 mil FiberTite-XTreme FB Roofing Systems can be installed by mechanically fastening the membrane with FiberTite Magnum Fasteners and Stress Plates or by adhering the “fleece back” membrane in FTR-290 low VOC solvent borne adhesive, FTR-390 water borne asphalt emulsion, FTR-490 water borne elastomeric adhesive, FTR CR-20, or hot asphalt to a variety of pre-approved substrates. 60 mil FiberTite-XTreme FB can also be installed in typical ballast configurations using conventional stone or paver ballast.

For specific installation recommendations and requirements, please consult the most current versions of Seaman Corporation’s Guide Specifications for the Installation of FiberTite Roofing Systems.

### PHYSICAL PROPERTIES (cont.)

Accelerated Weathering <i>Practice G 155 / xenon</i>	5000hr	>10000hr		
cracking (7x magnification)	none	none		
crazing (7x magnification)	none	none		
Accelerated Weathering <i>Practice G 154 / UVA</i>	5000hr	>10000hr		
cracking (7x magnification)	none	none		
crazing (7x magnification)	none	none		
Fungi Resistance <i>Practice G 21, 28 days</i>	no growth	no growth		
Sustained Growth Discoloration	none	none		
Abrasion Test, cycles <i>D 3389 H-18 wheel / 1,000 g load</i>	1,500	2,000+		
<b>Additional Physical Properties</b>				
Tensile Strength (psi) <i>ASTM D882</i>	> 9500			
Breaking Strength (lbs) <i>ASTM D751, Grab Method</i>	1096			
Puncture Resistance (lbs) <i>ASTM D751, Bursting Strength</i>	> 800			
Water Vapor Transmission <i>ASTM E96 proc. A (gm/m2/24hrs)</i>	1.3			
Shore A Hardness <i>ASTM D2240</i>	87			
Flame Resistance <i>MIL-C-20696C / Type II Class 2</i>	pass			
Oil Resistance, MIL-C-20696C <i>No swelling, cracking or leaking</i>	none			
Hydrocarbon Resistance, MIL-C-20696C <i>No swelling, cracking or leaking</i>	none			
<b>Energy Attributes</b>	<b>DC196 Off White</b>	<b>DC6 White</b>	<b>DC671 CR Gray</b>	<b>DC667 CR Tan</b>
Initial Solar Reflectance <i>ASTM C1549</i>	0.83	0.87	0.69	0.72
Solar Reflectance (3 yr aged) <i>ASTM C1549</i>	0.66	0.71	.61	.63
Initial Thermal Emittance <i>ASTM C1371</i>	0.85	0.85	0.89	0.88
Thermal Emittance (3 yr aged) <i>ASTM C1371</i>	0.74	0.84	.89	.89
Solar Reflective Index (SRI) <i>ASTM E1980</i>	104	110	84	88
Solar Reflective Index (SRI) (3 yr aged) <i>ASTM E1980</i>	76	86	73	76
Energy Star	YES	YES	YES	YES
LEED v4 - Heat Island Reduction <i>SS Credit</i>	1 Credit	1 Credit	1 Credit	1 Credit



**INTELLIGENT**  
ROOFING SOLUTIONS