



## Band annealing on Titanium fasteners

**Objective** Heating a titanium fastener to 1100-1450°F (593-788°C) for an annealing process.

**Material** 0.06" (1.5mm) high zone on a titanium fastener measuring 0.163-0.375" (4.14-9.52mm) in diameter and 0.5-3.0" (12.7-76.2mm) in length

**Temperature** 1100-1450°F (593-788°C)

**Frequency** 145 kHz

**Equipment**

- Ambrell 10.0 kW induction heating system, equipped with a remote workhead containing one 0.66µF capacitor.
- An induction heating coil designed and developed specifically for this application.

**Process** A three turn concentrator plate coil is used to heat the fastener for 0.2 seconds. This is an automated process that includes robotic placement of parts in the coil from a bowl fed track while Argon gas is flooded across the part to prevent oxidation. The parts are processed at a rate of 1000 parts per minute.

**Results/Benefits** Induction heating provides:

- Can be incorporated easily with pick and place robotics.
- Flameless process.
- Heating is limited to the specific area.

