

UMA 90

UMA 90 is an easy-to-use single cure resin with enhanced toughness, appropriate for use in prototypes and manufacturing jigs and fixtures.

Tensile Properties ASTM D638, Type V, 10 mm/min	GREEN STATE		UV-CURED	
	Metric	U.S.	Metric	U.S.
Tensile Modulus	731 ± 120 MPa	106 ± 17 ksi	2000 ± 100 MPa	290 ± 15 ksi
Ultimate Tensile Strength	25 ± 2 MPa	3.6 ± 0.3 ksi	46 ± 3 MPa	6.7 ± 0.4 ksi
Tensile Strength at Yield			46 ± 3 MPa	6.7 ± 0.4 ksi
Tensile Strain at Yield			5.7 ± 0.2%	
Elongation at Break	33 ± 2%		17 ± 2%	

Flexural Properties ASTM D790-B	GREEN STATE		UV-CURED	
	Metric	U.S.	Metric	U.S.
Flexural Stress at 5 % strain	26 ± 2 MPa	3.8 ± 0.3 ksi	79 ± 5 MPa	11.4 ± 0.7 ksi
Flexural Modulus (chord, 0.5-1 % strain)	656 ± 51 MPa	95 ± 7 ksi	2010 ± 119 MPa	291 ± 17 ksi

Impact Properties	UV-CURED	
	Metric	U.S.
Notched Izod (Machined), ASTM D256	33 ± 4 J/m	0.62 ± 0.07 ft-lb/in
Unnotched Izod, ASTM D4812	496 ± 141 J/m	9.29 ± 2.64 ft-lb/in

Thermal Properties ASTM D648	UV-CURED	
	Metric	U.S.
Heat Deflection Temperature @ 0.455 MPa/66 psi	51 °C	124 °F
Heat Deflection Temperature @ 1.82 MPa/264 psi	44 °C	111 °F

General Properties	UV-CURED	
	Metric	
Hardness, ASTM D2240	86, Shore D	
Density, ASTM D792	1.200 g/cm ³	
Density (liquid resin)	1.10 g/cm ³	

NOTES—Results in this data sheet are representative of specific sample generation and testing processes and may vary if the established protocols are not followed. Contact Carbon for the specific process used to generate the test samples to determine each of these values. Tensile and flexural data are average ± 1 standard deviation from 16 specimens; impact data used 10 specimens. The U.S. values are converted from Metric measurements and are for reference only.

The information in this document includes typical values from printing various parts and is intended for reference and comparison purposes only. This information should not be used for testing, design specification or quality control purposes. End-use material performance can be impacted by, but not limited to, design, processing, operating and end-use conditions, test conditions, color, etc. Actual values will vary with build conditions. In addition, product specifications are subject to change without notice.

This information and Carbon's technical advice are given to you in good faith but without warranty. The application, use and processing of these and other Carbon products by you are beyond Carbon's control and, therefore, entirely your own responsibility. Carbon products are only to be used by you subject to the terms of the written agreement by and between you and Carbon.

You are responsible for determining that the Carbon material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. CARBON MAKES NO WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR USE, OR NON-INFRINGEMENT. Further, it is expressly understood and agreed that you assume and hereby expressly release Carbon from all liability, in tort, contract or otherwise, incurred in connection with the use of Carbon products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Carbon. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.