

AXEL General Lubricating Grease Guide

The Most Advanced Lubricating Grease Technology Tailored to Your Needs



The table below presents a sample listing of our greases. Select your grease based on thickener technology, product properties, NLGI grade and temperature range. Our experienced lubricating grease experts can assist you in this selection or develop the most appropriate grease for your specific application need.

AXEL Product	Thickener	Product Properties	Colour	NLGI	DP (°C)	BO type	BOV (mm ² /s)	Solids	T-range (°C)	Approvals
Acinol 112 EPLT	Li	  		2	>180	Min	9	-	-50 to +90	-
Acinol 1300 EPS Green		 		0	>160	Min	40	-	-50 to +120	MAN 283 Li-P 00/000 MB Blatt 264.0
Acinol 1400		 		00	>160	Min	130	-	-35 to +100	-
Acinol 142		 		2	>180	Min	110	-	-30 to +120	-
Acinol 142 EPM		  		2	>180	Min	120	Graph/MoS ₂	-30 to +120	-
Acinol 152 EP		  		2	>180	Min	200	-	-30 to +120	MAN 283 Li-P 2 MB Blatt 267.0 BekaMax VOLVO Std 1277.18
Acinol 152 EPM3		   		2	>180	Min	200	MoS ₂	-30 to +120	MAN 285 Li-PF 2
Acinol 152 HQ Red		  		2	>180	Min	220	-	-30 to +120	LB
Acinol 1625 EP		  		2,5	>180	Min	290	-	-20 to +120	-
Acinol 1800 EP		  		00	>150	Min	1390	-	0 to +100	-
Acinol 1815 HD		  		1,5	>180	Min	1500	-	-20 to +120	-
Acinol 252 EP		  		2	>190	Min/Pol	310	-	-20 to +120	-
Acinol 621 LT		  		1	>180	PAO	20	-	-50 to +100	-
Acinol 8300 EP		   		00	>170	Alkylate	38	-	-50 to +100	MAN 283 Li-P 00/000 MB Blatt 264.0
Caliac 142 EP Green	Li-Ca	  		2	>180	Min	140	-	-20 to +120	-
Caliac 162 EPWR G3M2		  		2	>180	Min	670	Graph/MoS ₂	-20 to +120	-
Caliac 172 EP		   		2	>180	Min	1000	-	-20 to +120	-
Caliac 252 EP Green		   		2	>180	Min/Pol	310	-	-20 to +120	-
Claytac 0805 HTOG	Clay	  		0,5	N/A	Min	2100	Graph/CaCO ₃	-10 to +150	-
Claytac 642		  		2	N/A	PAO	120	-	-30 to +140	-
Hycal 152 EP	Anh-Ca	   		2	>140	Min	250	-	-30 to +110	-
Hycal 272 WR		   		2	>140	Min/Pol	1370	-	-30 to +120	-
Hycal 272 WRBF Neon Yellow		  		2	>140	Min/Pol	800	-	-30 to +120	-
Hycal 442 EPBD		   		2	>140	Veg/Pol	130	-	-30 to +80	SS 155470/2013 VGP
Hycal 762 EPBD		   		2	>140	Ester	490	-	-30 to +80	SS 155470/2013 VGP

Product Properties Key

-  Central Lubrication
-  Corrosion Protection
-  Environmental
-  Extreme Pressure
-  Heavy Loads
-  High Speed
-  High Temperature
-  Low Temperature
-  Multipurpose
-  Special Application
-  Water Resistant

Refer to our Condition Mats for more detail



AXEL General Lubricating Grease Guide

The Most Advanced Lubricating Grease Technology Tailored to Your Needs



The table below presents a sample listing of our greases. Select your grease based on thickener technology, product properties, NLGI grade and temperature range. Our experienced lubricating grease experts can assist you in this selection or develop the most appropriate grease for your specific application need.

AXEL Product	Thickener	Product Properties	Colour	NLGI	DP (°C)	BO type	BOV (mm²/s)	Solids	T-range (°C)	Approvals
Alassca 130 LTM5	Alassca	    		0	>260	Min	70	MoS ₂	-45 to +90	-
Alassca 1705 OG		     		0,5	>260	Min	850	-	-20 to +140	-
Alassca 762 BD		   		2	>260	Ester	700	Mix	-30 to +120	SS 155470/2013 VGP
Axellence 132 EP Red	Li-X	   		2	>260	Min	60	-	-30 to +140	-
Axellence 152 EP		  		2	>260	Min	200	-	-30 to +140	GC-LB VOLVO Std 1277.2
Axellence 152 EPS		  		2	>260	Min	200	-	-30 to +140	-
Axellence 152 HQ Blue		   		2	>260	Min	220	-	-20 to +140	GC-LB
Axellence 152 S Green		   		2	>260	Min	183	-	-20 to +140	MAN 284 Li-H 2 MB Blatt 265.1 Volvo Std 1277.2
Axellence 162 EPWRM3		   		2	>260	Min	400	MoS ₂	-20 to +140	-
Axellence 162 HQ		    		2	>260	Min	320	-	-20 to +140	GC-LB
Axellence 2615 EPHT		     		1,5	>260	Min/Pol	550	-	-20 to +140	-
Axellence 632 EPB		   		2	>260	PAO	44	-	-55 to +140	-
Axellence 642 EPB		   		2	>260	PAO	100	-	-40 to +150	-
Axellence 6525 EPB		  		2,5	>260	PAO	220	-	-40 to +150	-
Axellence 662 EPB		   		2	>260	PAO	460	-	-40 to +150	-
Axellence 681 EPB		   		1	>260	PAO/Pol	1750	-	-40 to +150	-
Axellence 752 EPBD		  		2	>260	Ester	295	-	-30 to +140	SS 155470/2013 VGP
Axellence 752 HT				2	>260	Ester	177	-	-20 to +160	-
Axelurea M 142 EM Blue		PU-M	 		2	>260	Min	105	-	-20 to +160
Axelurea T 142 EP Green	PU-T	  		2	>260	Min	100	-	-30 to +150	-
Axelurea T 150 EP Green		  		0	>230	Min	170	-	-30 to +150	-
Calsullence 142 M5	Ca-S-X	    		2	>250	Min	150	MoS ₂	-20 to +150	-
Calsullence 152 WR		    		2	>280	Min	290	-	-30 to +140	-
Calsullence 1615 WRM		    		1,5	>280	Min	400	MoS ₂	-20 to +140	-
Calsullence 630 M5		   		0	>260	PAO	46	MoS ₂	-40 to +140	-
Christolix 142 EP Green	Li-MS-X	  		2	>250	Min	130	-	-30 to +160	-
Dubbilit 2615 EP	Li-Bi-X	    		1,5	>260	Min/Pol	520	-	-20 to +150	-
Dubbilit 6615 EP		    		1,5	>260	PAO	460	-	-40 to +150	-
Noion 5215 EPB	Poly	    		1,5	>140	Min/Ester	26	-	-30 to +120	-
Noion 632 EPB		    		2	>140	PAO	47	-	-30 to +120	-
Stabox 9415	PTFE	 		1,5	N/A	PFPE	150	-	-20 to +200	-