

## Description

**FG850:** Staple Fiber processing, good barrier properties for film.

**Applications:** **FG850** is recommended for staple fiber, nonwovens, coextrusion, extrusion coating, injection molding

## Characteristics

	Method	Unit	Typical Value
<b>Rheological Properties<sup>(1)</sup></b>			
Melt Flow Index	D-1238	g/10 min	
190°C/2.16 kg			18.0
<b>Thermal Properties<sup>(1)</sup></b>			
Melting Point	D-3417	°F	263
<b>Other Physical Properties</b>			
Density	D 792	g/cm <sup>3</sup>	0.955
<b>Processing Recommendation</b>			
Extrusion Melt Temperature		°F	450-500

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

HDPE FG850 10/28/16