

Description

FG950: Bicomponent Spunbond and Fiber processing, good barrier properties for film.

Applications: **FG950** is recommended for bicomponent spunbond, bicomponent fiber, staple fiber, nonwovens, coextrusion, extrusion coating, injection molding

Characteristics

	Method	Unit	Typical Value
Rheological Properties⁽¹⁾			
Melt Flow Index	D-1238	g/10 min	
190°C/2.16 kg			30.0
Thermal Properties⁽¹⁾			
Melting Point	D-3417	°F	265
Other Physical Properties			
Density	D 792	g/cm ³	0.955
Processing Recommendation			
Extrusion Melt Temperature		°F	450-500

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

HDPE FG950 10/28/16