

	Method	Unit	Typical Value
<b>Resin Properties</b> <sup>(1)</sup>			
Melt Flow Index	D-1238	g/10 min	
190 °C/2.16 kg			30
Density	D-792	g/cm <sup>3</sup>	0.952
Melting Point	D-3417	°F	265
<b>Processing Recommendation</b>			
Extrusion Melt Temperature		°F	450 - 500

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

## Characteristics:

- Bicomponent spunbond and fiber processing
- Good barrier properties for film

## Applications:

- Bicomponent spunbond
- Bicomponent fiber
- Staple fiber
- Nonwovens
- Coextrusion
- Extrusion coating