

Christy® Pak Carbon Raschig Rings

FEATURES

- Resistant to a wide range of acids, alkalis and solvents
- High resistance to thermal shock
- High thermal conductivity
- Available in a variety of sizes
- High mechanical strength
- Fully carbonized – no extractable impurities
- ≥ 99% Carbon



PACKING DATA

Nominal OD		Density		Surface Area		Free Space	Wall Thickness
(in)	(mm)	(lb/ft ³)	(kg/m ³)	(ft ² /ft ³)	(m ² /m ³)	(%)	(mm)
1/2	(13)	37	(600)	107	(350)	72	2.4
3/4	(19)	36	(580)	61	(200)	64	3.8
1	(25)	34	(540)	67	(220)	66	4.7
1 1/2	(38)	31	(500)	38	(125)	68	6.8
2	(51)	25	(400)	37	(120)	75	6.0
3	(76)	32	(520)	18	(60)	74	10.0

Christy Catalytics, LLC offers a complete range of catalyst bed supports, tower packings and tower internals.