

Technical Data Sheet

NECAL 8608 PRESSURE SENSITIVE ADHESIVE

DESCRIPTION

NECAL 8608 is an extremely aggressive supported pressure sensitive adhesive.

FEATURES

NECAL 8608 is designed for adhesion to low energy surfaces (i.e. polyethylene and polypropylene) but especially for rough or textured surfaces.

PHYSICAL PROPERTIES

| Thickness (without liner): | 8.0 mils (total) | |
|---|--|------------------|
| Construction: | Modified acrylic low surface energy adhesive on both sides | |
| | of a non-woven polyester scrim | |
| Release Liner: | Available with P, W, H, J, VF, P1 or W1 liners | |
| 180° Peel from Stainless Steel (both passes): | >5 lbs. after 16 hour dwell (PSTC-101) | |
| Shear Adhesion (both passes): | >7 days (1 inch x 1 inch x 227 g @ 72°F) | |
| Temperature Range: | Application: | 50°F. Minimum |
| | Service: | -20°F. to 270°F. |

All tests conducted with a 2 mil PET backing

BONDING INSTRUCTIONS

Remove the release liner and apply to a clean, dry substrate. Use firm pressure to obtain maximum contact. Increasing application force will optimize bond strength to surface. The adhesive will reach maximum bond after 72 hours.

STORAGE DATA

The shelf life of this material is at least two years when stored at 72°F and 50% relative humidity. Increased temperatures and/or humidity will affect performance characteristics.

NOTICE

The information shown here represents typical values, which may vary with each application. The values are not intended to be a performance guarantee and are not intended to be utilized for setting specifications. Users should determine, prior to use, the suitability of this material for their application.

March-2018