



NECAL Corporation

Stick with Us

Technical Data Sheet

NECAL 9175 PRESSURE SENSITIVE ADHESIVE

DESCRIPTION

NECAL 9175 is an unsupported film of pressure sensitive adhesive displaying excellent bond characteristics and good initial tack.

FEATURES

NECAL 9175 will adhere to many substrates including aluminum, brass, steel, glass, enamels and plastics such as polystyrene, ABS, and acrylic. Because of its thickness NECAL 9175 is recommended for use on rough surfaces.

PHYSICAL PROPERTIES

Thickness (without liner):	4.0 mils acrylic adhesive
Release Liner:	Available with P, W, H, J, HD, VF, P1, HD-2 or W1 liners
180° Peel from Stainless Steel:	>4 lbs. after 16 hour dwell (PSTC-101)
Shear Adhesion:	>7 days (1 inch x 1 inch x 1000 g @ 72°F)
Temperature Range:	Application: 50°F. Minimum
	Service: -40°F. Minimum
	Short Term (minutes/hours): 400°F.
	Long Term (days/weeks): 300°F.

All tests conducted with a 2 mil PET backing

BONDING INSTRUCTIONS

Remove the release liner and apply to a clean, dry substrate. Use firm pressure to obtain maximum contact. Increasing application force will optimize bond strength to surface. The adhesive will reach maximum bond after 72 hours.

STORAGE DATA

The shelf life of this material is at least two years when stored at 72°F and 50% relative humidity. Increased temperatures and/or humidity will affect performance characteristics.

NOTICE

The information shown here represents typical values, which may vary with each application. The values are not intended to be a performance guarantee and are not intended to be utilized for setting specifications. Users should determine, prior to use, the suitability of this material for their application.



Standard UL 969

This material complies with
Component-Marking and Labeling
System Materials (PGGU2).

March-2018