

Stabilit America, Inc.

Technical Data

Acrylic Modified Polyester High Strength Panel

Product Description: Consisting of an 8oz Acrylic Modified Polyester Translucent Panel Chopped Strand+Woven Roving Fiberglass Reinforcement.

Property	ASTM Standard	Typical Values
Tensile Strength	D-638	25,500 psi
Tensile Modulus	D-638	1.2 x 106 psi
Flexural Strength	D-790	29,300 psi
Flexural Modulus	D-790	1.11 x 106 psi
Compressive Strength	D-695	28,905 psi
Burning rate	E-84	<2.5 in/min
Uniform Building Code Classification	E-84	CC2
Barcol Hardness	D-2583	40-50
Light Transmission	D-1494	55-60
U factor (with film coefficients)	N/A	1.1
Weight	D-3841	± 10%
Rib Height	D-3841	± 1/16 in
Length	D-3841	± 1/8 in
Width	D-3841	± 1/8 in

The information offered herein is offered without charge and is accepted as recipient's sole risk. Because of conditions of use vary and are beyond our knowledge and control. Stabilit America, Inc. dba Glasteel makes no representation about and is not responsible for the accuracy of the data, nor with toxicological effect or industrial hygiene requirements associated with particular uses—of any product or process described herein. Stabilit America, Inc. dba Glasteel requests that customers test and inspect our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from any law or patent inferred. All patents rights are reserved. The exclusive remedy for all proven claims is replacement of Stabilit America, Inc. dba Glasteel materials only.

Tel.: (877) 787-5467