## **Materials**

Material Profile:	Operating Temperatures:	
CAUTION! Operating temperature limitations are as follows:	Max.	Min.
Conductive Acetal: Tough, impact resistant, ductile. Good abrasion resistance and low friction surface. Generally inert, with good chemical resistance except for strong acids and oxidizing agents.	190°F 88°C	-20°F -29°C
<b>EPDM:</b> Shows very good water and chemical resistance. Has poor resistance to oils and solvents, but is fair in ketones and alcohols.	280°F 138°C	-40°F -40°C
FKM: (Fluorocarbon) Shows good resistance to a wide range of oils and solvents; especially all aliphatic, aromatic and halogenated hydrocarbons, acids, animal and vegetable oils. Hot water or hot aqueous solutions (over 70°F(21°C)) will attack FKM.	350°F 177°C	-40°F -40°C
Hytrel®: Good on acids, bases, amines and glycols at room temperatures only.	220°F 104°C	-20°F -29°C
Neoprene: All purpose. Resistance to vegetable oils. Generally not affected by moderate chemicals, fats, greases and many oils and solvents. Generally attacked by strong oxidizing acids, ketones, esters and nitro hydrocarbons and chlorinated aromatic hydrocarbons.	200°F 93°C	-10°F -23°C
Nitrile: General purpose, oil-resistant. Shows good solvent, oil, water and hydraulic fluid resistance. Should not be used with highly polar solvents like acetone and MEK, ozone, chlorinated hydrocarbons and nitro hydrocarbons.	190°F 88°C	-10°F -23°C
<b>Nylon:</b> 6/6 High strength and toughness over a wide temperature range. Moderate to good resistance to fuels, oils and chemicals.	180°F 82°C	32°F 0°C

Alloy C: Equal to ASTM494 CW-12M-1 specification for nickel and nickel alloy.

Polypropylene: A thermoplastic polymer. Moderate tensile

and flex strength. Resists stong acids and alkali. Attacked by chlorine, fuming nitric acid and other strong oxidizing agents. **PVDF:** (Polyvinylidene Fluoride) A durable fluoroplastic with

excellent chemical resistance. Excellent for UV applications.

Santoprene®: Injection molded thermoplastic elastomer with

no fabric layer. Long mechanical flex life. Excellent abrasion

UHMW PE: A thermoplastic that is highly resistant to a broad

range of chemicals. Exhibits outstanding abrasion and impact

resistance, along with environmental stress-cracking resistance. **Urethane:** Shows good resistance to abrasives. Has poor

Virgin PTFE: (PFA/TFE) Chemically inert, virtually impervious.

Very few chemicals are known to chemically react with PTFE;

molten alkali metals, turbulent liquid or gaseous fluorine and a few fluoro-chemicals such as chlorine trifluoride or oxygen difluoride which readily liberate free fluorine at elevated

High tensile strength and impact resistance.

resistance to most solvents and oils.

resistance.

temperatures.

Stainless Steel: Equal to or exceeding ASTM specification A743 CF-8M for corrosion resistant iron chromium, iron chromium nickel and nickel based alloy castings for general applications. Commonly referred to as 316 Stainless Steel in the pump industry.

For specific applications, always consult the Chemical Resistance Chart.

180°F

82°C

250°F

121°C

275°F

135°C

180°F

82°C

150°F

66°C

220°F

104°C

32°F

0°C

0°F

-18°C

-40°F

-40°C

-35°F

-37°C

32°F 0°C

-35°F

-37°C

Ambient temperature range: -20°C to +40°C

Process temperature range: -20°C to +80°C for models rated as category 1 equipment -20°C to +100°C for models rated as category 2 equipment

In addition, the ambient temperature range and the process temperature range do not exceed the operating temperature range of the applied non-metallic parts as listed in the manuals of the pumps.

