

Glove Chart



GlovePlus HD Blue Latex Exam Gloves

50/box, 10 boxes/case, M-XL


- Premium Latex
- Powder Free
- 12" long
- Exam Grade
- 13 mils thick
- Textured

Product Codes:

GPLHD44100 Medium
GPLHD46100 Large
GPLHD48100 X-Large

Applications:

Medical
Industrial
Chemical



GloveWorks HD Latex Exam Gloves

100/box, 10 boxes/case, S-XXL


- Premium Latex
- Powder Free
- Textured
- Exam Grade
- 8 mils thick
- Single Use Only

Product Codes:

ILHD42100 Small
ILHD44100 Medium
ILHD46100 Large
ILHD48100 X-Large
ILHD49100 XX-Large

Applications:

Chemical
Industrial
Medical



GloveWorks Latex Gloves

100/box, 10 boxes/case, XS-XL

- Select Latex
- Powder Free
- Ambidextrous
- Industrial Grade
- Textured

Product Codes:

TLF40100 X-Small
TLF42100 Small
TLF44100 Medium
TLF46100 Large
TLF48100 X-Large

Applications:

Industrial
Janitorial
Food Service



GlovePlus HD Heavy Duty Nitrile Exam Gloves

50/box, 10 boxes/case, M-XL

- Premium Nitrile
- Powder Free
- 12" long
- Latex Free
- Exam Grade
- 8 mils thick
- Textured

Product Codes:

GPNDH64100 Medium
GPNDH66100 Large
GPNDH68100 X-Large

Applications:

Medical
Automotive
Industrial



Xtreme Nitrile Gloves

100/box, 10 boxes/case, M-XL

- Premium Nitrile
- Powder Free
- Latex Free
- Industrial Grade
- Textured

Product Codes:

XNPF42100 Small
XNPF44100 Medium
XNPF46100 Large
XNPF48100 X-Large
XNPF49100 XX-Large

Applications:

Industrial
Automotive
Chemical



GlovePlus Black Nitrile Gloves

100/box, 10 boxes/case, M-XL

- Select Nitrile
- Powder Free
- Latex Free
- Industrial Grade
- Textured

Product Codes:

GPNB44100 Medium
GPNB46100 Large
GPNB48100 Extra Large
GPNB49100 XX-Large

Applications:

Automotive
Industrial
Chemical



Xtreme Extra Long Nitrile Exam Gloves

100/box, 10 boxes/case, S-XL

- Select Nitrile
- Powder Free
- Textured
- Exam Grade
- 12" long
- Latex Free

Product Codes:

XNPFL42100 Small
XNPFL44100 Medium
XNPFL46100 Large
XNPFL48100 X-Large

Applications:

Lab
Industrial
Medical



Xtreme X3 Nitrile Gloves

100/box, 10 boxes/case, S-XXL

- Standard Nitrile
- Powder Free
- Latex Free
- Industrial Grade
- Textured
- Chlorinated

Product Codes:

X342100 Small
X344100 Medium
X346100 Large
X348100 X-Large
X349100 XX-Large

Applications:

Industrial
Janitorial
Food Service



Ammex Black Nitrile Exam Gloves

100/box, 10 boxes/case, S-XL

- Premium Nitrile
- Powder Free
- Latex Free
- Exam Grade
- Textured

Product Codes:

ABNPF42100 Small
ABNPF44100 Medium
ABNPF46100 Large
ABNPF48100 X-Large

Applications:

Industrial
Lab
Medical



Ammex Nitrile Exam Gloves

100/box, 10 boxes/case, S-XL

- Premium Nitrile
- Powder Free
- Textured
- Exam Grade
- Latex Free

Product Codes:

APFN42100 Small
APFN44100 Medium
APFN46100 Large
APFN48100 X-Large

Applications:

Dental
Medical
Janitorial



Ammex Indigo Nitrile Exam Gloves

100/box, 10 boxes/case, S-XL

- Premium Nitrile
- Powder Free
- Latex Free
- Exam Grade
- Textured

Product Codes:

AINPF42100 Small
AINPF44100 Medium
AINPF46100 Large
AINPF48100 X-Large

Applications:

Medical
Dental
Lab



chemex
industries, inc.

CHEMICAL RESISTANCE CHART

THIS CHEMICAL RESISTANCE CHART IS FOR ADVISORY USE ONLY!

Conditions, exposure times, chemical concentrations and residues may affect glove performance.
It is strongly advised that on-site testing of all gloves is important to help determine safe usage.

Chemical Resistance	Latex	Nitrile	Vinyl	Chemical Resistance	Latex	Nitrile	Vinyl
Acetaldehyde, 99.5%	Recommended	Limited Use	Not Recommended	Hydrochloric Acid, 38%	Recommended	Recommended	Recommended
Acetic Acid	Recommended	Recommended	Recommended	Hydrofluoric Acid, 48%	Recommended	Recommended	Recommended
Acetone, 99.5%	Recommended	Not Recommended	Not Recommended	Hydrogen Peroxide, 30%	Recommended	Recommended	Recommended
Acetonitrile, 99%	Recommended	Recommended	Not Recommended	Hydroquinone	Recommended	Recommended	Recommended
Acrylic Acid, 99%	Recommended	Limited Use	Not Rated	Iodine	Recommended	Recommended	Recommended
Ammonium Fluoride, 40%	Recommended	Recommended	Recommended	Isobutyl Alcohol, 99%	Recommended	Recommended	Recommended
Ammonium Hydroxide, 85%	Recommended	Not Recommended	Recommended	Iso-Octane, 99%	Limited Use	Recommended	Not Recommended
Amyl Acetate, 100%	Not Recommended	Recommended	Limited Use	Isopropanol	Not Rated	Recommended	Not Rated
Amyl Alcohol, 99%	Recommended	Recommended	Limited Use	Isopropyl Alcohol, 99%	Limited Use	Recommended	Recommended
Aniline, 99%	Limited Use	Not Recommended	Limited Use	Isopropyl Benzene	Not Rated	Recommended	Not Rated
Animal Fats	Not Recommended	Recommended	Recommended	Kerosene, 100%	Recommended	Recommended	Not Recommended
Aqua Regia	Not Recommended	Recommended	Recommended	Lactic Acid, 85%	Recommended	Recommended	Recommended
Battery Acid	Recommended	Recommended	Recommended	Lauric Acid, 36%	Recommended	Recommended	Limited Use
Benzaldehyde, 99.5%	Limited Use	Not Recommended	Not Recommended	Linoleic Acid	Not Recommended	Recommended	Recommended
Benzene	Not Recommended	Recommended	Limited Use	Linseed Oil	Not Recommended	Recommended	Recommended
Benzyl Chloride	Limited Use	Recommended	Not Recommended	Maleic Acid, 100%	Recommended	Recommended	Recommended
Bromine	Recommended	Not Rated	Recommended	Methanol	Not Rated	Recommended	Not Rated
Bromopropionic Acid, Sat.	Recommended	Recommended	Not Rated	Methyl Acetate	Not Recommended	Not Recommended	Not Rated
Butane	Not Recommended	Recommended	Not Recommended	Methyl Alcohol, 99.9%	Recommended	Recommended	Recommended
2-Butoxyethanol	Not Rated	Recommended	Not Rated	Methylamine, 40%	Recommended	Recommended	Recommended
Butyl Acetate, 99%	Not Recommended	Limited Use	Not Recommended	Methyl-Butyl Ether, 99.8%	Not Recommended	Recommended	Not Rated
Butyl Alcohol, 99%	Recommended	Recommended	Recommended	Methyl Cellosolve, 99%	Limited Use	Limited Use	Not Recommended
Butyl Cellosolve, 99%	Recommended	Recommended	Not Recommended	Methylamine	Recommended	Recommended	Recommended
Butyrolactone, 99%	Recommended	Not Recommended	Not Rated	Methyl Chloride	Not Recommended	Not Recommended	Not Recommended
Calcium Hypochlorite	Not Recommended	Recommended	Recommended	Methylene Chloride	Limited Use	Recommended	Limited Use
Carbolic Acid	Not Recommended	Not Recommended	Recommended	Methyl Ethyl Ketone, 99%	Limited Use	Not Recommended	Not Recommended
Carbon Dichloride	Not Rated	Recommended	Not Rated	Methyl Isobutyl Ketone	Limited Use	Not Recommended	Not Rated
Carbon Disulfide, 99.9%	Not Recommended	Limited Use	Not Recommended	Methyl Methacrylate	Not Recommended	Not Recommended	Not Rated
Carbon Tetrachloride, 99%	Not Recommended	Recommended	Limited Use	Methyl-T-Butyl Ether	Not Rated	Recommended	Not Rated
Castor Oil	Recommended	Recommended	Recommended	Mineral Oil	Not Recommended	Recommended	Limited Use
Cellosolve Acetate, 99%	Recommended	Recommended	Not Recommended	Mineral Spirits, 100%	Not Recommended	Recommended	Not Recommended
Cellosolve Solvent	Recommended	Recommended	Not Rated	Monoethanolamine, 99%	Limited Use	Recommended	Recommended
Chlorine	Recommended	Recommended	Recommended	Morpholine, 99%	Limited Use	Not Recommended	Limited Use
Chloroacetone	Limited Use	Not Rated	Not Recommended	Muriatic Acid, 100%	Recommended	Recommended	Recommended
Chloroform	Not Recommended	Recommended	Not Recommended	Naphtha VM&P, 100%	Not Recommended	Recommended	Not Recommended
Chloronaphthalenes	Not Rated	Limited Use	Not Rated	N-Methyl-2 Pyrrolidone, 99%	Limited Use	Not Recommended	Not Rated
Chlorothene VG	Not Rated	Limited Use	Not Recommended	Naphthalene	Recommended	Recommended	Recommended
Chromic Acid, 50%	Not Recommended	Limited Use	Recommended	Nitric Acid, 10%	Recommended	Recommended	Recommended
Citric Acid, 10%	Recommended	Recommended	Recommended	Nitric Acid, 70%	Not Recommended	Not Recommended	Limited Use
Cottonseed Oil	Not Recommended	Recommended	Recommended	Nitrobenzene, 99%	Limited Use	Not Recommended	Not Recommended
Croosol	Not Recommended	Recommended	Limited Use	Nitromethane, 95.5%	Recommended	Not Recommended	Not Recommended
Cunene	Not Rated	Recommended	Not Rated	Nitropropane, 95.5%	Recommended	Not Recommended	Not Rated
Cutting Oil	Limited Use	Recommended	Not Recommended	Octyl Alcohol, 99%	Recommended	Recommended	Recommended
Cyclohexane	Not Recommended	Recommended	Not Recommended	Oleic Acid, 99%	Recommended	Recommended	Recommended
Cyclohexanol, 98%	Recommended	Recommended	Recommended	Oxalic Acid, 12.5%	Recommended	Recommended	Recommended
Diacetone Alcohol, 99%	Limited Use	Recommended	Limited Use	Paint Remover	Limited Use	Recommended	Not Recommended
Dibutyl Phthalate, 99%	Limited Use	Recommended	Not Recommended	Palmitic Acid, Sat.	Recommended	Recommended	Recommended
Diamine	Not Rated	Recommended	Not Rated	Pentachlorophenol, 35%	Not Recommended	Recommended	Not Rated
Diethylamine, 99%	Not Recommended	Limited Use	Not Recommended	Pentane, 98%	Not Recommended	Recommended	Recommended
Diethyl Ether	Limited Use	Recommended	Not Recommended	Perchloric Acid, 60%	Limited Use	Limited Use	Recommended
Di-Isobutyl Ketone, 80%	Limited Use	Recommended	Recommended	Perchloroethylene	Not Rated	Recommended	Not Rated
Dimethyl Acetamide, 99%	Limited Use	Not Recommended	Not Rated	Perholfium Ether	Not Rated	Recommended	Not Rated
N,N-Dimethyl Formamide, 99%	Recommended	Not Recommended	Not Recommended	Phenol, 90%	Recommended	Not Recommended	Recommended
Dimethyl Sulfoxide, 99%	Recommended	Recommended	Not Recommended	Phosphoric Acid, 85%	Recommended	Recommended	Recommended
Diocetyl Phthalate, 99%	Limited Use	Recommended	Not Rated	Picric Acid	Recommended	Recommended	Recommended
1,4-Dioxane, 99.9%	Limited Use	Not Recommended	Limited Use	Potassium Hydroxide, 50%	Recommended	Recommended	Recommended
Epichlorohydrin, 99%	Limited Use	Not Recommended	Not Rated	Printing Ink	Recommended	Recommended	Limited Use
Ethanol	Not Rated	Recommended	Not Rated	Propyl Acetate, 99%	Not Recommended	Limited Use	Not Recommended
2-Ethoxyethanol	Not Rated	Recommended	Not Rated	Propyl Alcohol, 96%	Recommended	Recommended	Limited Use
Ethyl Acetate, 99%	Limited Use	Not Recommended	Not Rated	Propylene Oxide	Not Recommended	Not Rated	Not Rated
Ethyl Alcohol, 90%	Recommended	Recommended	Limited Use	Pyridine, 99%	Limited Use	Not Recommended	Not Rated
Ethyl Ether, 99%	Limited Use	Recommended	Recommended	Rubber Solvent, 100%	Not Recommended	Recommended	Not Recommended
Ethylene Dichloride	Not Recommended	Recommended	Not Recommended	Rule Solvent	Not Rated	Recommended	Not Rated
Ethylene Glycol, 99%	Recommended	Recommended	Recommended	Sodium Hydroxide, 50%	Recommended	Recommended	Recommended
Ethyl Glycol Ether, 99%	Limited Use	Limited Use	Not Rated	Sodium Hypochlorite	Recommended	Limited Use	Recommended
Ethylene Trichloride	Not Recommended	Not Recommended	Not Rated	Stoddard Solvent, 99%	Not Recommended	Not Recommended	Recommended
Fluorine	Recommended	Not Rated	Recommended	Sulfuric Acid, 95%	Recommended	Limited Use	Recommended
Formaldehyde, 99%	Recommended	Recommended	Recommended	Tannic Acid, 37.5%	Recommended	Recommended	Recommended
Formalin Solution	Not Rated	Recommended	Not Rated	1,1,2,2-Tetrachloroethane, 99%	Not Recommended	Not Recommended	Not Rated
Formic Acid, 95%	Recommended	Limited Use	Recommended	Tetrachloroethylene, 100%	Not Recommended	Not Recommended	Recommended
Freon TF, 99%	Not Recommended	Limited Use	Limited Use	Toluene, 99%	Not Recommended	Not Recommended	Limited Use
Furfural, 99%	Recommended	Not Recommended	Not Recommended	Toluene Di-Isocyanate	Not Recommended	Not Rated	Not Recommended
Gasoline, 100%	Not Recommended	Recommended	Limited Use	1,1,1-Trichloroethane, 99%	Not Recommended	Not Recommended	Not Rated
Glycerine	Recommended	Recommended	Recommended	Trichloroethylene	Not Recommended	Recommended	Limited Use
Glycerol	Recommended	Recommended	Recommended	Tricresyl Phosphate, 90%	Not Recommended	Recommended	Limited Use
Heptane	Not Rated	Recommended	Not Rated	Triethanolamine, 85%	Limited Use	Recommended	Recommended
Hexamethyldisilazine, 97%	Recommended	Recommended	Not Rated	Tung Oil	Not Rated	Recommended	Limited Use
Hexane, 99%	Not Recommended	Recommended	Not Recommended	Turbine Oil	Not Recommended	Recommended	Limited Use
Hydraulic Fluid-Petrol Based	Not Recommended	Recommended	Recommended	Turpentine, 100%	Not Recommended	Recommended	Not Recommended
Hydraulic Fluid- Ester Based	Not Recommended	Not Recommended	Not Recommended	Vegetable Oil	Not Recommended	Recommended	Limited Use
Hydrazine, 65%	Recommended	Recommended	Recommended	Xylene	Not Recommended	Limited Use	Not Recommended